# FLEXIBLE HOSES

# GENERAL CATALOG



# **TOTAKU Hose Handling Precautions**

Hoses are flexible and convenient piping materials, but unexpected accidents may occur depending on the conditions of use. Be sure to carefully read and adhere to the handling precautions beforehand. Please understand that our company cannot be held responsible for any damages resulting from failure to follow these precautions.

# 1. Usage Precautions (Fluid: Water, Liquids)

- 1. The allowable pressure of the hose indicates the maximum pressure it can handle when it is either straight or bent with a radius larger than the minimum allowable bend radius. Therefore, it must not be used at pressures exceeding this limit. Note that this does not represent the maximum continuous operating pressure (working pressure).
- 2. Allowable pressure is not the same as the maximum operating pressure. Please refer to the following table to determine the operating pressure (working pressure) accordingly.

How to Calculate Operating Pressure	Hose Type	Safety Factor
Operating Pressure × Safety Factor ≤ Allowable Pressure	TOTAKU ECO Series, TOTAKU Fluoro Series, SD Hose Series (General Use, Food-Grade, Oil- Resistant, AS, Grounded), TOTAKU HERAN Series	2.0
	Line Power Series	1.5

Note: For information on the safety factors and allowable pressure of each hose, please refer to the respective product pages for each hose.

- 3. The performance of the hose (allowable pressure, operating pressure, bending, etc.) is significantly affected by the fluid and surrounding temperatures. Please note that for some hoses, at a fluid temperature of 50°C (122°F), the allowable and operating pressures may decrease to less than half of the values at 25°C (77°F) when the ambient temperature is 30°C (86°F).
- 4. Certain fluids—such as drugs, solvents, acids, and alkalis may cause changes to the hose material, including hardening or swelling. In these cases, ensure the safety factor is calculated as: operating pressure × 3.0 ≤ allowable pressure. *Hoses must never be used for highly toxic chemicals, highly concentrated acids or alkalis, explosive or flammable gases, or other hazardous substances.* Using hoses in such conditions poses a significant risk of hose failure, which could lead to severe injury or health risks.
- 5. Do not bury hoses underground. External pressure and internal pressure creep may cause the reinforcement layer to crack, leading to potential leaks.
- 6. Avoid using hoses inside sleeve pipes. Expansion during pressurization may cause the hose to bend or meander, potentially leading to cracks in the reinforcement layer or leaks.

7. When used in the riser section of a submersible pump, a water hammer may occur when the pump stops. In such cases, set the pump pressure with a higher safety factor as described in 4. A water hammer may cause the hose to fail, leading to potential accidents.



- 8. When operating a valve, open or close it slowly over at least three seconds to avoid creating shock pressure. Closing a valve too quickly, especially at the end of the hose, can generate shock pressure and may result in hose failure. As a rule of thumb, shock pressure can be estimated by converting the flow velocity (ft/sec [m/sec]) into pressure (psi [MPa]) and adding it to the operating pressure. This occurs when the valve is closed abruptly. *Note: Use a flow velocity of 6.6 ft/sec (2 m/sec) or less as a guideline.*
- 9. When hoses are used outdoors for extended periods, they may experience UV degradation, leading to discoloration (darkening), hardening, or ozone-induced cracking. If you notice signs of discoloration or cracking, replace the hose with a new one as soon as possible.
- 10. Hoses should be regarded as consumable items.
- **11.** Do not use hoses for compressed air piping. Under certain conditions, they may burst, posing a risk of accidents.
- 12. Never use general-purpose hoses for pharmaceutical applications. Doing so may result in legal penalties under applicable laws.
- 13. If the hose will be used for transporting highpurity chemicals, please consult us. For example, when used for transporting pure water, the hose itself will not be affected; however, components of the hose may leach into the water, potentially contaminating its purity.
- 14. For food-related applications, please use hoses classified as food-grade. Using any other type of hose may result in legal penalties under applicable laws.
- 15. When using food-grade hoses for transporting drinking water or food products, ensure that the interior of the hose is thoroughly cleaned before use.

# 2. Precautions for Hose Installation

- Hoses are consumable items. Hoses gradually deteriorate over time with extended use. Perform regular inspections (see 5. Inspection) and discontinue use immediately if any abnormalities are detected. Replace with a new hose as needed.
- 2. When installing hoses, take precautions to ensure that, in the event of failure, the damage does not pose a risk to people or surrounding equipment (such as electrical systems).
- 3. Hoses expand and contract due to internal pressure, so ensure adequate slack when installing them.
- 4. When using hoses in fixed piping, operate them at no more than half of their allowable pressure. Operating near the allowable pressure may cause significant hose expansion, resulting in reduced bend radius in certain areas, which could lead to damage. For fixed piping applications, consider using the LINE POWER series, which minimizes expansion under pressure.
- 5. Hose twisting can lead to performance degradation. If twisting occurs due to equipment oscillation or rotation, use swivel joints, loose flanges, or cap nut-type joints.
- 6. Using a hose with a small bend radius reduces its allowable pressure. If (operating pressure)×(safety factor) approaches the hose's allowable pressure, ensure the bend radius is greater than the minimum allowable bend radius.
- 7. Connecting a hose horizontally to equipment at a high position can cause its weight to concentrate bending stress near the connection point, leading to early failure. To prevent this, support the area near the fittings, use an elbow joint, or route the hose vertically.
- 8. If the hose is connected horizontally to equipment positioned high up, its own weight can place stress near the connection point, potentially causing it to break prematurely. To prevent this, support the hose near the fittings, use an elbow joint, or install the hose vertically.
- Ensure that 1–2 meters of hose remain in a straight position on both the inlet and outlet sides of the pump (piping). Additionally, secure the hose to prevent tension caused by pump movement or vibrations.
- 10. If the hose is subject to stretching, contraction, vibration, or repetitive motion that causes it to rub against other objects, protect the hose by using supports, protective wires, or guard springs.
- 11. Avoid using hoses in a horizontally suspended position (e.g., ceiling-mounted horizontal piping). The hose's own weight, fluid weight, and pressure-induced elongation can cause sagging or bending, which may lead to damage.

- 12. Avoid applying external shocks to the hose.
- 13. Do not step on the hose or run over it with a vehicle.
- 14. Do not pull the hose to move machinery, nor move machinery or vehicles while the hose is still attached.
- 15. When installing long hoses (165 feet [50 meters] or more), be aware that differences in elevation and pressure loss may prevent the required flow rate from being achieved. Please exercise caution in such cases

# 3. Precautions for Hose Storage

# 3-1. Storing Hoses After Use

- 1. After using the hose, remove any residue inside by rinsing it with water or other appropriate methods.
- 2. Rinse the hose with water to remove any deposits from the inner surface, and cap both ends of the hose.
- 3. Store the hose in a location away from direct sunlight.

# 3-2. Storage as Stock

- 1. Store in a cool, dark place with low humidity, away from direct sunlight.
- 2. Cap both ends of the hose to prevent dust and debris from entering.
- 3. Do not stack hoses in large quantities or place heavy objects on top of them.
- 4. Do not store hoses in an excessively bent state. Whenever possible, store them indoors in a straight position on a flat floor.
- 5. When PVC hoses come into contact with rubber products, the PVC hoses may discolor. To prevent this, avoid storing them in contact with rubber products. *Note: Some products may discolor. For details, please refer to the "Caution" section for each product.*

# 4. Precautions for Hose Transportation

- 1. Do not drag hoses on the ground or over concrete during transportation.
- 2. Do not throw or subject hoses to impacts during loading and unloading.
- 3. When lifting hoses with a crane or similar equipment, avoid single-point lifting. Use a lifting beam and nylon slings for multi-point lifting.

# 5. Inspection (To Prevent Accidents and Ensure Safe Hose Usage)

# 5-1. Daily Inspections

Perform a visual inspection of the hose before use. If any abnormalities are detected, replace the hose or take appropriate measures, such as removing the affected section.

# 5-2. Periodic Inspections

Conduct a thorough visual inspection and a hydrostatic pressure test at or below the allowable pressure every three months, following the steps outlined below.

# (a) Visual Inspection

If any of the following abnormalities are found, the hose is unsuitable for use and should be replaced with a new one:

- Abnormalities near fittings: Localized stretching, swelling, bending, or leakage.
- External damage: Significant surface damage, reinforcement layer cracks, or cracks in the grooves.
- Hose abnormalities: Flattening, deformation, kinking, internal swelling, or delamination.
- Other severe deterioration: Hardening, swelling, cracking, etc.

# (b) Hydrostatic Pressure Test

Use the hose's initial expansion during pressurization (based on our inspection report data or your own initial pressure test data and product condition) as a reference. If the values from periodic inspections exceed 1.5 times the initial value, stop using the hose immediately and replace it with a new one. *Additionally, always perform the test at or below the allowable pressure.* Testing at excessively high pressures may shorten the hose's lifespan.

# 6. Precautions for Fittings and Bands

 i. When using hoses other than ducting hoses, use a nipple with an outer diameter that is approximately the same as or slightly larger than the hose's inner diameter. If the nipple's outer diameter is smaller than the hose's inner diameter, it may result in water leakage or fitting detachment, potentially causing accidents.

ii. For ducting hoses, the nipple's outer diameter must be smaller than the hose's inner diameter, so be sure to select the correct size.

- 2. Some commercially available fittings may not be compatible for installation. Please consult us in advance.
- 3. The hose's pressure resistance varies depending on the type, number, and tightening force of the bands. Choose the appropriate bands based on the hose's operating conditions.

# 7. Others

- 1. Discard used hoses as industrial waste.
- 2. Our products are solid materials with a fixed shape and are therefore not subject to SDS requirements. (However, reference data is available upon request.)

Hose Selection Guidelines	- Please rev	view the belo	w items thorou	ghly when co	ntacting us.
---------------------------	--------------	---------------	----------------	--------------	--------------

Usage Specifications Fluid Operating Conditions	Purpose					
	Device Name					
		Inner Diameter	Actual size (in [mm])			
	Dimensions	Outer Diameter	Actual size (in [mm])			
		Length	Total length including fittings			
Specifications		Flange/Nipple	ANSI/ASME (JIS), K Flange, SCollar with Thread, etc. For other special types, please contact us.			
	Fittings	Clamping Method	SY band, Reber clamp, TOTAKU power band, outer tube crimping, etc. For other special tightening methods, please consult us.			
Fluid	State		Gas, liquid, solid, slurry, etc.			
	<b>Composition &amp; Concentration</b>	C	omposition and Concentration			
	Temperature		Fluid temperature (°F [°C])			
	Flow Rate & Flow Velocity	Flow Rate: GPI	M / SCFM (m³/h)   Flow Velocity: ft/sec (m/s)			
	Pressure	Maximum Operating Pressure	Discharge pressure: psi (MPa) Suction (vacuum) pressure: inHg (kPa)			
		Peak Pressure	Pump pressure, surge pressure, etc.			
		Outside Air Temperature	°F (°C)			
Operating	<b>Environmental Conditions</b>	Atmosphere	Outdoor, indoor, offshore, underwater, etc.			
Conditions		External Pressure	psi (MPa)			
		Installation Dimensions	Installation type and motion diagram, etc.			
	Bending Conditions	Minimum Bending Radius	Must meet or exceed the allowable bending radius, etc.			
		Operating Cycle	Repetitive bending cycle, etc.			
	Usage Time	Continuo	ous use time and intermittent cycle, etc.			
Performance	Past Usage Record	Manufacturer, pr	roduct name, time in use (operating time), etc.			
Regulations	Applicable Laws & Standards	F	ood sanitation regulations, etc.			

# **Explanation of Hose Physical Property Terms**

# Allowable Pressure (at Room Temperature)

Allowable pressure represents the maximum pressure a hose can withstand when in a straight position or bent with a radius larger than the minimum allowable bend radius. It must not be used at pressures exceeding this limit. This is not the maximum continuous operating pressure (working pressure). The allowable pressure decreases at higher operating temperatures and also varies depending on the hose size, fitting and band combination, and operating environment.

The allowable pressure is not the maximum operating pressure. Therefore, use the following formula as a reference when determining the operating pressure (working pressure):

(Operating Pressure) × (Safety Factor) ≤ (Allowable Pressure)

## Allowable Vacuum Pressure (Room Temperature)

This is the maximum vacuum pressure that can be applied to the hose at room temperature. The hose cannot be used at vacuum pressures exceeding this limit. Additionally, the allowable vacuum pressure decreases at higher operating temperatures. According to the Japanese Industrial Standard (JIS Z 8703), room temperature is defined as  $68^{\circ}F \pm 27^{\circ}F$  ( $20^{\circ}C \pm 15^{\circ}C$ ).

### Allowable Bending Radius

This is the minimum bending radius the hose can safely accommodate. Using the hose at a smaller bending radius is not permitted.

### How the Radius is Measured

The bending radius is measured from the center of the bend to the centerline of the hose.

Bendin		
radius	a 🗸 / / a	\ \
Tuulus	/ $/$	\
1	Ы	
	$\sim$	



# **TOTAKU Non-PVC Hoses ECO Series**

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

# Featured Products

ECO LINE-HO 100°	C 02	ECO SD-C	09
SHIMETAC for TOT	AKU	ECO DUCT	10
ECO LINE-HO 100°	C 03	ECO DUCT-AS	11
ECO LINE	04		
ECO LINE-HO	05		
SHIMETAC for TOTA	AKU		
ECO LINE	06		
ECO PP-SPRING	07		
FCO SD-AS	08		-

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

# TOTAKU ECO LINE-HO 100°C

Part Number - 22188



**Standard Dimensions and Properties** 

#### Features

- Suitable for transporting oils, fatty foods, and general food products.
- Complies with standards for food and additives established by the Japanese Ministry of Health and Labour and Welfare (Notification No. 370). But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Can be cleaned with hot water at temperatures up to 212°F (100°C) or with 95% ethanol, ensuring hygienic use.
- /Safe for incineration after use without emitting harmful gases. (Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.)
- Semi-transparent construction allows for easy inspection of transported materials.
- Reinforced with a reinforcing fiber, offering pressure resistance up to 101.5 psi (0.7 MPa).

# Applications

- Suitable for transporting edible oils, fatty foods, sake, shochu, and other alcoholic beverages, as well as soft drinks and various liquids or powders.
- Ideal for hygienic piping applications, such as transporting purified water.
- Designed for transporting hot water or similar liquids at temperatures ۲ below 212°F (100°C). (Refer to the table below for pressure resistance performance at temperatures above 104°F [40°C].)

Nominal Inner Outer Pitch Referen Diameter Diameter Weigh	e Length Allowable Pressure (to the center axis (at room temperature) of the hose)
inch mm inch mm inch mm inch mm lbs/ft g	/m feet m psi MPa inch mm
1 25 1.00 25.4 1.52 38.6 0.30 7.5 0.31 4	60 65/164 20/50 101.53 0.70 4.72 120
1.5 38 1.50 38.0 2.17 55.0 0.39 10.0 0.57 8	50 65/164 20/50 101.53 0.70 9.45 240
2 50 2.00 50.8 2.72 69.0 0.43 11.0 0.81 1	210 65/164 20/50 101.53 0.70 11.81 300

Nom	inal	Allowable Pressure										
Diam	leter	104°F to (40°C to	o 140°F o 60°C)	140°F to (60°C to	o 176°F o 80°C)	176°F to (80°C to	176°F to 212°F (80°C to 100°C)					
inch	mm	inch	mm	inch	mm	inch	mm					
1	25	87.02	0.60	72.52	0.50	58.02	0.40					
1.5	38	87.02	0.60	72.52	0.50	58.02	0.40					
2	50	79.77	0.55	58.02	0.40	43.51	0.30					

The recommended operating temperature range is 32°F to 212°F (0°C to 100°C). However, allowable pressure may vary depending on the operating temperature and installation method.

# **Recommended Fitting Installation Examples**



SHIMETAC (for IDF Ferrule)



**EPDM Corrugated Sealing** with Stainless Steel Crimping (for IDF Ferrule)

# **Operating Temperature Range:**

°F: 32 to 212 °C: 0 to 100

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

Scan, tap, or touch for product videos



Product Overview

# SHIMETAC for TOTAKU ECO LINE-HO 100°C

Applicable Sizes: 1.5 inches ( $\phi$ 38 mm) and 2 inches ( $\phi$ 50 mm)

#### Part number 92413 Material: Fiber-Reinforced Polypropylene

## Features

- Made from resin, ensuring a lightweight design.
- Rust-free due to its resin construction.
- Equipped with Stainless Steel 304 bolts, flat washers, and nuts.
- Reliable pressure resistance performance.
- Fittings are removable for easy cleaning. •
- Designed with a secure structure to prevent detachment. •

# Notes

- Be sure to use the *dedicated fittings* for SHIMETAC.
- The fittings shown below are examples.

# Pressure Resistance Performance at 212°F (100°C)

			Processing Methods										
Nom Diam	ninal neter	EPDM Co Sealing wi Steel C	orrugated ith Stainless rrimping	Bar Tighte	ıd ning	SHIMETAC Tightening							
inch	mm	inch	mm	inch	mm	inch	mm						
1	25	58.02	0.40	14.50	0.10	—	_						
1.5	38	58.02	0.40	14.50	0.10	58.02	0.40						
2	50	43.51	0.30	14.50	0.10	43.51	0.30						

# **Dedicated Fittings for SHIMETAC**



Part Number 92312

**IDF Ferrule with SHIMETAC shank** (Stainless Steel)

Part Number 92332



Camlock 633-ETS (Stainless Steel)

(Stainless Steel)

M1 SHIMETAC shank

Part Number 92416



TS Flange with SHIMETAC shank (PVC)

Scan, tap,

or touch for

product videos

Part Number 92305



Flange with SHIMETAC shank (Stainless Steel)

Part Number 92417



Loose Flange with SHIMETAC shank





Camlock 633-CTS (Stainless Steel)



(Polypropylene) (Flange Part: Structural Steel)







Installation Method

# TOTAKU ECO LINE

Part Number - 22166





#### TOTAKU ECO LINE with Grounding Wire Part Number - 22167



Note: This product is made to order. Please contact us for more information.

# **Standard Dimensions and Properties**

## Features

- Safe for use in food applications. Note: Not suitable for transporting foods or liquids containing oils or fats.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- The U.S. standard is currently under development.
- Can be cleaned with hot water<sup>1</sup> and 95% ethanol, ensuring hygienic use.
- Safe for incineration after use without emitting harmful gases<sup>2</sup> (Incineration ash residue is less than 0.1%).
- Semi-transparent construction allows for easy inspection of transported materials.
- Flexible design enables easy handling during use.
- It is equipped with a reinforcement fiber, providing an allowable pressure of 72.5 psi (0.50 MPa).

# Applications

- Suitable for transporting alcoholic beverages such as sake and shochu, as well as soft drinks.
- Ideal for transporting other food products, including liquids and powders.
- Designed for general water suction and discharge applications.

### Cautions

• Do not use or store outdoors for extended periods.

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Refer Wei	Reference Weight		Length		Allowable Pressure (at room temperature)		Bend Radius axis of the hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.44	36.7	0.31	7.8	0.24	350	164	50	72.52	0.50	4.72	120
1.25	32	1.26	32.0	1.73	44.0	0.35	8.8	0.30	445	164	50	72.52	0.50	5.91	150
1.5	38	1.50	38.0	2.01	51.0	0.37	9.3	0.39	580	164	50	72.52	0.50	8.27	210
2	50	2.00	50.8	2.57	65.2	0.40	10.2	0.54	800	164	50	72.52	0.50	9.45	240
2.5	65	2.50	63.5	3.17	80.5	0.55	14.0	0.74	1105	65/164	20/50	72.52	0.50	12.99	330
3	75	3.00	76.2	3 76	95 5	0 59	15.0	1 03	1530	65/164	20/50	72 52	0.50	15 35	390

The recommended operating temperature range is  $32^{\circ}F$  to  $122^{\circ}F$  ( $0^{\circ}C$  to  $50^{\circ}C$ ). However, allowable pressure may vary depending on the operating temperature and installation method. For continuous use, keep the temperature below  $104^{\circ}F$  ( $40^{\circ}C$ ).

# Operating Temperature Range:

°F: 32 to 122 °C: 0 to 50

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg
  - (-0.1 MPa) is feasible at room temperature.

#### Additional Notes:

<sup>1</sup> Hot water cleaning should be performed under the following conditions: temperature below 176°F (80°C), pressure below 14.5 psi (0.1 MPa), and a pressurization time of 3 minutes or less.

<sup>2</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.

# TOTAKU ECO LINE-HO

Part Number - 22168





## Features

- Suitable for transporting oils, fatty foods, and general food products.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Can be cleaned with hot water<sup>1</sup> and 95% ethanol, ensuring hygienic use.
- Safe for incineration after use without emitting harmful gases<sup>2</sup> (Incineration ash residue is less than 0.1%).
- Semi-transparent construction allows for easy inspection of transported materials.
- It is equipped with a reinforcement fiber, providing an allowable pressure of 72.5 psi (0.50 MPa).

## Applications

• Suitable for transporting edible oils, fatty foods, sake, shochu, and other alcoholic beverages, as well as soft drinks and various liquids or powders.

### Cautions

• Do not use or store outdoors for extended periods.

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.47	37.4	0.31	7.8	0.24	360	164	50	72.52	0.50	4.72	120
1.25	32	1.26	32.0	1.73	44.0	0.35	9.0	0.31	455	164	50	72.52	0.50	5.91	150
1.5	38	1.50	38.0	2.01	51.0	0.39	10.0	0.39	580	164	50	72.52	0.50	9.45	240
2	50	2.00	50.8	2.55	64.8	0.41	10.5	0.55	820	164	50	72.52	0.50	11.81	300

The recommended operating temperature range is 32°F to 140°F (0°C to 60°C). However, allowable pressure may vary depending on the operating temperature and installation method. For continuous use, keep the temperature below 122°F (50°C).

### Operating Temperature Range:

Notes:

°F: 32 to 140 °C: 0 to 60

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

#### Additional Notes:

<sup>1</sup> Hot water cleaning should be performed under the following conditions: temperature below 176°F (80°C), pressure below 14.5 psi (0.1 MPa), and a pressurization time of 3 minutes or less.

<sup>2</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.

# Standard Dimensions and Properties

# SHIMETAC for TOTAKU ECO LINE

Applicable Sizes: 1 inch (\$\phi25 mm)\*, 1.5 inches (\$\phi38 mm), 2 inches (\$\phi50 mm), 2.5 inches (\$\phi56 mm), 3 inches (\$\phi75 mm)\$

## SHIMETAC for TOTAKU ECO LINE and TOTAKU ECO LINE-HO

\*1 inch (φ25 mm) is compatible with Line Ace



Part Number 92311 Material: Fiber-Reinforced Polypropylene

#### TOTAKU ECO LINE

Allowable Pressure: 72.5 psi (0.5 MPa) or less (at room temperature)

Hot Water Wash: 14.5 psi (0.1 MPa) or less (up to 176°F [80°C], within 3 minutes)

# **Dedicated Fittings for SHIMETAC**



M1 SHIMETAC shank (Stainless Steel) Also available in Steel Structure



Camlock 633-ETS (Stainless Steel)



TOTAKU ECO LINE-HO

Allowable Pressure: 72.5 psi (0.5 MPa) or less (at room temperature)

Hot Water Wash: 14.5 psi (0.1 MPa) or less (up to 176°F [80°C], within 30 minutes)

Part Number 92313

(Stainless Steel)

Part Number 92417

(Polypropylene)

Scan, tap,

or touch for

product videos

**IDF Ferrule with SHIMETAC shank** 

Loose Flange with SHIMETAC shank

(Flange Part: Steel Structure)

# Features

- Made from resin, ensuring a lightweight design.
- Rust-free due to its resin construction.
- Equipped with Stainless Steel 304 bolts, flat washers, and nuts.
- Reliable pressure resistance performance.
- Fittings are removable for easy cleaning.
- Designed with a secure structure to prevent detachment. •

# Notes

- Be sure to use the *dedicated fittings* for SHIMETAC.
- The fittings shown below are examples. •

Stainless Steel Bolt

# Suggested Food-Grade Assembly

TOTAKU ECO LINE. (1 inch [φ25 mm], 1.5 inches [φ38 mm], 2 inches [φ50 mm], 2.5 inches [\$45 mm], 3 inches [\$475 mm]) TOTAKU ECO LINE-HO:





(Stainless Steel)

SHIMETAC for TOTAKU ECO LINE



Part Number 92333



Camlock 633-CTS (Stainless Steel)





Flange with SHIMETAC shank (Stainless Steel)







Installation Method

# **TOTAKU ECO PP-SPRING**

Applicable Sizes: 1 inch (\$\phi25 mm), 1.25 inches (\$\phi32 mm), 1.5 inches (\$\phi38 mm), 2 inches (\$\phi50 mm), 1.25 inches (\$\phi32 mm), 1.5 inches (\$\phi38 mm), 2 inches (\$\phi50 mm), 1.25 inches (\$\phi32 mm), 1.5 inches (\$\phi38 mm), 2 inches (\$\phi50 mm), 1.5 inches (\$\phi38 mm), 2 inches (\$\p 2.5 inches (φ65 mm), 3 inches (φ75 mm)

**ECO PP Spring Installation Example** 





# Applications

- Designed for use as a corrugated sealing material when securing TOTAKU ECO LINE with flat bands or similar fasteners.
- Ideal for preventing localized bending near fittings.

# Example of TOTAKU ECO LINE in Use





# TOTAKU ECO SD-AS

Part Number - 22183



SHIMETAC for TOTAKU ECO LINE is now available! (Applicable Sizes: 1.5 inches (\$\varphi 38 mm))

(Applicable Sizes: 1.5 inches (φ38 m to 3 inches (φ75 mm))



#### Features

- Safe for use in food applications. Note: Not suitable for transporting foods or liquids containing oils or fats.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Safe for incineration after use without emitting harmful gases.<sup>1</sup>
- The smooth inner surface boosts transport efficiency.
  - Ensures strong anti-static properties.
- Lightweight, flexible, and offers excellent abrasion resistance.
- Semi-transparent construction allows for easy inspection of transported materials.

# Applications

- Ideal for transporting resin pellets used in food packaging, toys, and other applications.
- Suitable for transporting granular and powdered food products.
- Appropriate for transporting pharmaceuticals.
- Also used for transporting non-food granular and powdered materials.

# Cautions

• Do not use or store outdoors for extended periods.

Standard	Dimensions	s and P	ropertie	35
			-	

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1.5	38	1.50	38.0	1.89	48.0	0.35	9.0	0.23	340	164	50	14.50	0.10	5.91	150
2	50	2.00	50.8	2.44	62.0	0.39	10.0	0.37	550	164	50	14.50	0.10	7.68	195
2.5	65	2.50	63.5	2.99	76.0	0.56	14.3	0.47	695	65/164	20/50	14.50	0.10	10.04	255
3	75	3.00	76.2	3.62	92.0	0.62	15.8	0.64	950	65	20	14.50	0.10	10.04	255
4	100	4.00	101.6	4.67	118.5	0.71	18.0	1.08	1600	65	20	14.50	0.10	17.72	450

The recommended operating temperature range is  $32^{\circ}F$  to  $122^{\circ}F$  ( $0^{\circ}C$  to  $50^{\circ}C$ ). However, allowable pressure may vary depending on the operating temperature and installation method. For continuous use, keep the temperature below  $104^{\circ}F$  ( $40^{\circ}C$ ).

# Operating Temperature Range:

°F: 32 to 122 °C: 0 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

Additional Notes:

<sup>1</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.



# TOTAKU ECO SD-C

Part Number - 22182





#### Features

- Safe for use in food applications. Note: Not suitable for transporting foods or liquids containing oils or fats.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Provides outstanding heat resistance and flexibility.
- Can be cleaned with hot water<sup>1</sup> and 95% ethanol, ensuring hygienic use.
- Safe for incineration after use without emitting harmful gases.<sup>2</sup>
- Lightweight, and offers excellent abrasion resistance.
- Features smooth surfaces on both the interior and exterior.
- Semi-transparent construction allows for easy inspection of transported materials.

### Applications

- <sup>9</sup> Suitable for transporting alcoholic beverages such as sake and shochu, as well as soft drinks.
- Ideal for transporting food products and others.
- Designed for general water suction and discharge applications.

### Cautions

• Do not use or store outdoors for extended periods.

Nom Diam	iinal ieter	In Dian	ner neter	Ou Diam	ter neter	Refer Wei	ence ght	Leng	jth	Allowable (at room te	e Pressure emperature)	Allowable Bend Radius (to the center axis of the hose)		
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm	
1.5	38	1.50	38.0	1.83	46.6	0.33	485	164	50	43.51	0.30	9.45	240	
2	50	2.00	50.8	2.39	60.6	0.54	805	164	50	29.01	0.20	14.17	360	

The recommended operating temperature range is 32°F to 122°F (0°C to 50°C). However, allowable pressure may vary depending on the operating temperature and installation method. For continuous use, keep the temperature below 104°F (40°C).

# Operating Temperature Range:

**Standard Dimensions and Properties** 

°F: 32 to 122 °C: 0 to 50

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5inHg
   (-0.1 MPa) is feasible at room temperature.

#### Additional Notes:

' Hot water cleaning should be performed under the following conditions: temperature below 176°F (80°C), pressure below 14.5 psi (0.1 MPa), and a pressurization time of 3 minutes or less.

<sup>2</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.

# TOTAKU ECO DUCT



# Features

- Lightweight and flexible, allowing for easy handling.
- Safe for use in food applications.
   Note: Not suitable for transporting foods or liquids containing oils or fats.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Exceptional bending durability. (No defects observed after 1,000,000 bending cycles)
- Transparent construction allows for easy inspection of transported materials
- Safe for incineration after use without emitting harmful gases.<sup>1</sup> (Incineration ash residue is 0.05% or less)

# Applications

- Suitable for air supply and exhaust in equipment and machinery.
- Appropriate for use in intake and exhaust systems of food-grade machinery.
- Ideal for air supply and exhaust in cleanrooms and other environments requiring low particle emission.
- Suitable for drainage purposes (for surface-level drainage).

### Cautions

• Do not use or store outdoors for extended periods.

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Pi	tch	Refei Wei	rence ight	Len	gth	Allowable (at room te	e Pressure mperature)	Allov Depress (at room te	vable urization mperature)	Allowable (to the co the	Bend Radius enter axis of e hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.25	32	1.26	32.0	1.50	38.0	0.30	7.5	0.11	170	98	30	5.80	0.04	-14.97	-50.7	1.57	40
1.5	38	1.50	38.0	1.77	45.0	0.31	7.8	0.16	235	98	30	5.80	0.04	-14.97	-50.7	1.97	50
2	50	2.00	50.8	2.32	59.0	0.39	10.0	0.22	325	98	30	5.80	0.04	-14.97	-50.7	2.36	60
2.5	65	2.50	63.5	2.83	72.0	0.49	12.5	0.27	405	98	30	4.35	0.03	-14.97	-50.7	2.95	75
3	75	3.00	76.2	3.35	85.0	0.51	13.0	0.32	470	98	30	4.35	0.03	-9.74	-33.0	3.54	90
3.5	90	3.50	88.9	3.90	99.0	0.53	13.5	0.39	575	98	30	4.35	0.03	-5.91	-20.0	3.54	90
4	100	4.00	101.6	4.39	111.5	0.59	15.0	0.43	635	98	30	4.35	0.03	-5.17	-17.5	4.33	110
5	125	5.00	127.0	5.45	138.5	0.83	21.0	0.66	975	65	20	2.90	0.02	-3.69	-12.5	5.31	135
6	150	6.00	152.4	6.46	164.0	0.79	20.0	0.76	1125	65	20	2.90	0.02	-3.69	-12.5	6.30	160
8	200	8.00	203.2	8.50	216.0	0.89	22.5	1.04	1545	65	20	1.45	0.01	-1.77	-6.0	8.27	210
10	250	9.92	252.0	10.67	271.0	1.02	26.0	2.00	2975	32	10	1.45	0.01	-1.18	-4.0	11.81	300
12	300	11.93	303.0	12.68	322.0	1.02	26.0	2.51	3735	32	10	1.45	0.01	-0.74	-2.5	13.78	350

This product uses materials designed to minimize dust generation; however, under certain conditions (such as temperature, fluid type, or pressure), particle emission may still occur. Please verify emission characteristics based on your operating conditions before use.

#### Operating Temperature Range:

**Standard Dimensions and Properties** 

#### Notes:

°F: 32 to 122 °C: 0 to 50

• The permissible pressure varies with operating temperature.

Additional Notes:

<sup>1</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.

10 of 11 | TOTAKU Non-PVC Hose ECO Series

#### Scan, tap, or touch for product videos



Product Overview

# TOTAKU ECO DUCT-AS

<section-header>

**Standard Dimensions and Properties** 

# Features

- Lightweight and flexible, allowing for easy handling.
- Safe for use in food applications.
   Note: Not suitable for transporting foods or liquids containing oils or fats.
- Meets the standards for food and additives set by the Japanese Ministry of Health, Labour and Welfare (Notification No. 370), excluding elution testing for fatty and oily foods. But they do not meet U.S. standards. They are currently under development, so please contact us for more details.
- Exceptional bending durability. (No defects observed after 1,000,000 bending cycles)
- Transparent construction allows for easy inspection of transported materials
- Safe for incineration after use without emitting harmful gases.<sup>1</sup> (Incineration ash residue is 0.05% or less)

# Applications

- Suitable for air supply and exhaust in equipment and machinery.
- Appropriate for use in intake and exhaust systems of food-grade machinery.

Scan, tap,

or touch for

product videos

Static

Electricity

Prevention

- Ideal for air supply and exhaust in cleanrooms and other environments requiring low particle emission.
- Suitable for drainage purposes (for surface-level drainage).

### Cautions

• Do not use or store outdoors for extended periods.

Non Dian	ninal neter	In Diar	ner neter	Ou Diar	iter neter	Pi	tch	Refei Wei	rence ight	Len	gth	Allowable (at room ter	Pressure mperature)	Allow Depressu (at room tel	vable urization mperature)	Allowable (to the ce the	Bend Radius enter axis of hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.5	38	1.50	38.0	1.77	45.0	0.31	7.8	0.15	220	98	30	5.80	0.04	-14.97	-50.7	1.97	50
2	50	2.00	50.8	2.32	59.0	0.39	10.0	0.22	325	98	30	5.80	0.04	-14.97	-50.7	2.36	60
2.5	65	2.50	63.5	2.83	72.0	0.49	12.5	0.27	405	98	30	4.35	0.03	-14.97	-50.7	2.95	75
3	75	3.00	76.2	3.35	85.0	0.51	13.0	0.32	470	98	30	4.35	0.03	-9.74	-33.0	3.54	90
4	100	4.00	101.6	4.39	111.5	0.59	15.0	0.43	635	98	30	4.35	0.03	-5.17	-17.5	4.33	110
5	125	5.00	127.0	5.45	138.5	0.83	21.0	0.54	805	65	20	2.90	0.02	-3.69	-12.5	5.31	135
6	150	6.00	152.4	6.46	164.0	0.79	20.0	0.71	1055	65	20	2.90	0.02	-3.69	-12.5	6.30	160
8	200	8.00	203.2	8.50	216.0	0.89	22.5	0.97	1440	65	20	1.45	0.01	-1.77	-6.0	8.27	210

This product uses materials designed to minimize dust generation; however, under certain conditions (such as temperature, fluid type, or pressure), particle emission may still occur. Please verify emission characteristics based on your operating conditions before use.

### Operating Temperature Range:

#### Notes:

°F: -4 to 122 °C: -20 to 50

 The permissible pressure varies with operating temperature.

Additional Notes:

<sup>1</sup> Includes hydrogen chloride, sulfur oxides, nitrogen oxides, hydrogen cyanide, and ammonia.

11 of 11 | TOTAKU Non-PVC Hose ECO Series



# TOTAKU FLUORO Hoses

Inner Surface: Fluororesin

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

# **Featured Products**

FLUORO-A02FLUORO-C03SHIMETAC for<br/>TOTAKU FLUORO04

TOTAKU FLUORO Chemicals Resistance Table 05

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

# TOTAKU FLUORO-A

Part Number - 23120- 050





TOTAKU FLUORO-A with Grounding Wire Part Number - 23121- 050



Note: This product is made to order. Please contact us for more information.

# **Standard Dimensions and Properties**

Features

- Outstanding resistance to chemicals due to the low reactivity of PTFE resin.
- Fluids have low adhesion to the surface, which provides excellent water-repellent properties for effortless cleaning.
- Designed for safe and easy connections.
- Low leaching minimizes liquid alteration, making it ideal for transporting chemicals.
- Lightweight, constructed entirely from resin.

# Applications

- Suitable for both suction and delivery applications.
- Transportation of chemical products.
- Transportation of paints.

# Cautions

- Not suitable for medical or pharmaceutical applications. Therefore, safety for such uses cannot be guaranteed.
- Not suitable for transporting powders or granules.
- Hot water washing should be done under the following conditions: temperature under 176°F (80°C), pressure below 14.5 psi (0.1 MPa), and pressurization time limited to 3 minutes or less.

Nom Diam	ninal neter	In Dian	ner neter	Outer D	liameter	Pi	tch	Referenc	e Weight	Allowable (at room te	Pressure mperature)	Allowable (to the center	Bend Radius r axis of the hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	psi	MPa	inch	mm
2	50	2.00	50.8	2.39	60.6	0.39	10.0	0.52 (0.53)*	780 (785)*	36.26	0.25	11.81	300

\*Values in parentheses refer to TOTAKU FLUORO-A Grounded

# Operating Temperature Range:

°F: 14 to 122 °C: -10 to 50

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

# TOTAKU FLUORO-C





TOTAKU FLUORO-C with Grounding Wire Part Number - 23123



Note: This product is made to order. Please contact us for more information.

# **Standard Dimensions and Properties**

# Features (inner surface made with fluororesin)

- Outstanding resistance to chemicals due to the low reactivity of PTFE resin.
- Fluids have low adhesion to the surface, which provides excellent water-repellent properties for effortless cleaning.
- Designed for safe and easy connections.
- Low leaching minimizes liquid alteration, making it ideal for transporting chemicals.
- Lightweight, constructed entirely from resin.

# Applications

- Suitable for both suction and delivery applications.
- Transportation of chemical products.
- Transportation of paints.

# Cautions

- Not suitable for medical or pharmaceutical applications. Therefore, safety for such uses cannot be guaranteed.
- Not suitable for transporting powders or granules.
- Hot water washing should be done under the following conditions: temperature under 176°F (80°C), pressure below 14.5 psi (0.1 MPa), and pressurization time limited to 3 minutes or less.

Nom Diam	ninal neter	In Diar	ner neter	Οι Diar	iter neter	Refei Wei	rence ght	Allowable (at room ter	Pressure mperature)	Allowable (to the cente	e Bend Radius r axis of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	psi	MPa	inch	mm
1	25	1.00	25.4	1.27	32.2	0.28 (0.29)*	420 (430)*	72.52	0.50	9.45	240
1.5	38	1.50	38.0	1.82	46.2	0.50 (0.51)*	740 (755)*	58.02	0.40	13.78	350

\*Values in parentheses refer to TOTAKU FLUORO-C Grounded

# Operating Temperature Range:

°F: 14 to 122 °C: -10 to 50

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

# **SHIMETAC for TOTAKU FLUORO**

Applicable Sizes: 1 in ( $\phi$ 25) to 2 in ( $\phi$ 50)

# SHIMETAC for TOTAKU FLUORO

1 in (φ25), 1.5 in (φ38) Part No. 92378 2 in (φ50) Part No. 92377-050 Material: Cast Stainless Steel (SCS14, Equivalent to AISI 316



# Features

- Made with an AISI 316 (SUS316) holder for superior corrosion resistance.
- Equipped with bolts and nuts made of AISI 304 (SUS304).
- Features a silicone gasket.
- Improved pressure resistance with a special antipullout structure.
- Easy to connect on-site.
- Can be reused repeatedly.

# Notes

- Be sure to use the *dedicated fittings* for SHIMETAC.
- The fittings shown are examples.

# SHIMETAC for TOTAKU FLUORO Features a Specialized Anti-Pullout Structure





# **Dedicated Fittings for SHIMETAC**



M1 SHIMETAC Shank F (AISI 316) Sizes: 1 in (φ25) to 2 in (φ50)



IDF Ferrule SHIMETAC Shank F (AISI 316) Sizes: 1 in ( $\phi$ 25) to 2 in ( $\phi$ 50)

# Improved Design to Prevent Fluid Pooling at the Nipple Tip

The internal tapered nipple design has been enhanced by reshaping the nipple tip, effectively resolving issues caused by fluid pooling.



# **Hose Installation Examples**

# For SHIMETAC

IDF Ferrule with SHIMETAC Shank F



# For Crimping

For IDF Ferrule







For M1



Scan, tap, or touch for product videos





Installation Method

# **TOTAKU FLUORO Chemicals Resistance Table**

					. /			
	Oil, Solvents, and Chemicals [Concentration (wt%), Temperature (°F [°C])]	Тохіс	Hazardous	Dangerous	Fluoro (Inner Layer)	Resin N	AISI 304 (SUS304)	AISI 316 (SUS304)
A	Acetaldehyde			$\checkmark$	0	0	0	0
	Acetic Acid (100%, Room Temperature)			✓	0	0	-	-
	Acetone			$\checkmark$	0	•	0	0
	Acetonitrile		~	~	0	-	-	-
	Acetophenone				0	0	0	0
	Acrylonitrile		~	~	0	0	0	0
	Alum				0	0	-	-
	Aluminum Chloride				0	0	X	Х
	Aluminum Fluoride				0	0	X	Х
	Ammonium Carbonate				0	0	0	0
	Ammonium Chloride				0	0	•	<b>♦</b>
	Ammonium Hydroxide (Ammonia Water)		$\checkmark$		0	0	0	0
	Ammonium Nitrate				0	0	0	0
	Amyl Alcohol			$\checkmark$	0	0	0	0
	Aniline		$\checkmark$		0	•	0	0
	Aqua Regia		$\checkmark$		0	•	X	X
	Arsenic Acid	✓			0	0	-	_
В	Barium Chloride		✓		0	0	Х	0
	Barium Hydroxide		✓		0	0	0	0
	Benzaldehyde			✓	0	•	•	٠
	Benzene			$\checkmark$	0	•	0	0
	Benzoic Acid				0	0	•	•
	Benzoyl Chloride				0	•	-	-
	Benzyl Alcohol				0	0	•	•
	Borax				0	0	_	0
	Boric Acid				0	0	0	0
	Boron Trifluoride		$\checkmark$		0	0	-	_
	Bromine		✓		0	Х	Х	x
	Butyl Acetate			✓	0	•	0	0
	Butyl Alcohol			✓	0	0	0	0
С	Calcium Chloride				0	0	0	0
	Calcium Nitrate				0	0	-	-
	Carbon Disulfide		✓	✓	0	•	0	0
	Carbon Tetrachloride		✓		0	Х	0	0
	Cellosolve			✓	0	•	0	0
	Chlorobenzene			✓	0	X	_	-
	Chloroform		✓		0	•	0	0
	Chlorosulfonic Acid		✓		0	x	x	•
	Chromic Acid (25%, Room Temperature)		✓		0	0	X	•
	Citric Acid				0	0	0	0
	Copper Chloride		1		0	0	•	•
	Creosote Oil				0	_	0	•
	Cresol		1		0	0	•	0
	Cyclohexane			1	0	•	0	0
	Cyclohexanol			·	0	•	0	0
	Cyclohexanon			· ·	0	•	0	0
D				✓	0	•	0	0
U				,	0	_	0	0
	Dibutylamine			1	0	_	5	5
	Diethyl Ether (Ethyl Ether)			·	0	-	-	-
				•	0	•		
	Dimensi Filinalate				U	-	-	-

Toxic: Chemicals designated as toxic substances. Hazardous: Chemicals designated as hazardous substances.

Dangerous: Class 4 special flammable substances, Class 1 petroleum substances, alcohols,

and Class 2 petroleum-based materials prone to generating static electricity. Resin N: Resin-made nipples for SHIMETAC. AISI 304 (SUS304): Bolts and nuts for SHIMETAC. AISI 316 (SUS316): Stainless steel holders and Nipple F for SHIMETAC.

Note: The classifications used in this table follow Japanese standards. Please contact us for details.

Symbol Explanations:

**0** : No or minimal impact.

♦ : Significant impact (may still be usable under certain conditions).

X : Not suitable for use. -/: No data available.

# **TOTAKU FLUORO Chemicals Resistance Table**

	Oil, Solvents, and Chemicals [Concentration (wt%), Temperature (°F [°C])]	Тохіс	Hazardous	Dangerous	Fluoro (Inner Layer)	Resin N	AISI 304 (SUS304)	AISI 316 (SUS304)
	Dimethylacetamide			$\checkmark$	0	-	-	-
	Dimethylformamide (DMF)			$\checkmark$	0	0	-	0
	Dioctyl Phthalate				0	•	0	0
	Dioxane			$\checkmark$	<b>♦</b>	•	-	-
Е	Epichlorohydrin		✓	✓	-	-	0	0
	Ethanol (Ethyl Alcohol)			$\checkmark$	0	0	0	0
	Ethyl Acetate		$\checkmark$	$\checkmark$	0	•	0	0
	Ethylene Dichloride			$\checkmark$	0	•	0	0
	Ethylene Glycol				0	0	0	0
	Ethylene Oxide		$\checkmark$		<b>♦</b>	0	0	0
	Ethylenediamine			✓	0	0	0	0
F	Fatty Acids				0	•	0	0
	Ferric Chloride Solution (38%, Room Temperature)				0	0	X	Х
	Formaldehyde (40%, Room Temperature)		$\checkmark$		0	0	0	0
	Formic Acid (50%, Room Temperature)				0	0	•	0
	Furan			$\checkmark$	-	_	_	0
	Furfuryl Alcohol			✓	0	Х	0	0
G	Gasoline			✓	0	۲	0	0
	Glucose				0	0	0	0
	Glycerin				0	0	0	0
	Glycolic Acid				0	_	_	_
н	Hentane			$\checkmark$	0	•	0	0
	Hexane			✓	0	0	0	0
	Hydrazine	✓			0	-	0	0
	Hydrobromic Acid (20% Room Temperature)		✓		0	0	v v	v v
	Hydrochloric Acid (38%, Room Temperature)		✓		0	0	X	X
	Hydrofluoric Acid (20%, Room Temperature)	1	•		0	0	~	~
	Hydrogan Baravida (20%, Koom Temperature)	•	1		0	0	0	0
T	Isooctano		•	<u></u>	0	•	0	0
1	Keresene				0	•	0	0
				•	0	•	v	0
			-		0	0	~	0
	Lead Nitrate		•		0	0	U	U
			•		0	0	-	-
N 4	Linseed Oil Magnasium Chlorida				0	0	•	0
IVI	Magnesium Undrewide				0	0	•	0
	Magnesium Hydroxide				0	0	•	0
	Mareira Mareira	1			0	0	•	•
	Mercury	•			0	0	U	U
	Mercury(II) Chloride	v	1	1	0	0	X	X
			•	•	0	0	0	0
	Methyl Ethyl Ketone (MEK)		<b>v</b>	<b>v</b>	0	0	0	0
	Methyl Isobutyl Ketone			~	0	•	0	0
	Methylene Chloride				0	•	-	-
	Mineral Oil (ASTM No. 3)				0	0	0	0
	Monochloroacetic Acid		✓		0	0	-	-
Ν	Naphtha			$\checkmark$	0	•	0	0
	Naphthalene				0	0	0	0
	Nickel Chloride				0	0	•	0
	Nitric Acid (60%, Room Temperature)		✓		0	X	0	0
	Nitrobenzene		$\checkmark$		0	0	0	0
	N-Methylaniline		$\checkmark$		0	-	-	-

Toxic: Chemicals designated as toxic substances. Hazardous: Chemicals designated as hazardous substances. Dangerous: Class 4 special flammable substances, Class 1 petroleum substances, alcohols,

and Class 2 petroleum-based materials prone to generating static electricity. Resin N: Resin-made nipples for SHIMETAC. AISI 304 (SUS304): Bolts and nuts for SHIMETAC. AISI 316 (SUS316): Stainless steel holders and Nipple F for SHIMETAC.

Note: The classifications used in this table follow Japanese standards. Please contact us for details.

Symbol Explanations:

**0** : No or minimal impact.

♦ : Significant impact (may still be usable under certain conditions).

X : Not suitable for use. -/: No data available.

# **TOTAKU FLUORO Chemicals Resistance Table**

	Oil, Solvents, and Chemicals [Concentration (wt%), Temperature (°F [°C])]	Тохіс	Hazardous	Dangerous	Fluoro (Inner Layer)	Resin N	AISI 304 (SUS304)	AISI 316 (SUS304)
	N-Methylpyrrolidone				0	-	-	-
0	Octane			$\checkmark$	0	-	-	-
	Octene			$\checkmark$	0	-	-	-
	Oleic Acid				0	0	0	0
	Oxalic Acid		$\checkmark$		0	0	•	•
Ρ	Perchloric Acid				0	•	X	X
	Perchloroethylene				0	•	-	•
	Phenol (Room Temperature)		$\checkmark$		0	-	0	0
	Phenylhydrazine				0	-	-	-
	Phosphoric Acid (50%, Room Temperature)				0	0	0	0
	Phosphorus Oxychloride	$\checkmark$			0	-	-	-
	Phosphorus Trichloride	✓			0	-	-	-
	Phthalic Acid				0	-	-	-
	Potassium Chloride				0	0	0	0
	Potassium Hydroxide (30%, Room Temperature)		$\checkmark$		0	0	•	•
	Potassium Nitrate				0	0	•	•
	Potassium Permanganate (5%, Room Temperature)				0	0	0	0
	Propyl Alcohol			$\checkmark$	0	0	0	0
	Propylene Oxide			$\checkmark$	0	-	-	-
	Pyridine			$\checkmark$	0	•	-	•
S	Salad Oil				0	-	0	0
	Salicylic Acid				0	0	0	0
	Seawater				0	0	0	0
	Silicon Tetrachloride				0	-	-	-
	Silver Nitrate		✓		0	0	•	0
	Sodium Carbonate				0	0	0	0
	Sodium Chloride (Salt)				0	0	•	•
	Sodium Hydroxide (Caustic Soda) (10%, Room Temperature)		✓		0	0	0	0
	Sodium Hypochlorite (5%, Room Temperature)				0	0	X	•
	Sodium Nitrate				0	0	0	0
	Sodium Silicate				0	0	-	0
	Sodium Sulfite				0	0	0	0
	Sodium Thiosulfate				0	0	-	0
	Stannous Chloride (Tin(II) Chloride)		✓		0	0	-	-
	Stearic Acid				0	0	0	0
	Sulfur				0	0	0	0
	Sulfuric Acid (98%, Room Temperature)		$\checkmark$		0	•	X	X
	Sulfurous Acid (10%, Room Temperature)				0	0	•	0
Т	Tetrahydrofuran (THF)			✓	•	•	-	0
	Toluene		✓	✓	0	•	0	0
	Tributylamine				0	-	-	-
	Trichloroacetic Acid		$\checkmark$		0	0	•	<b>♦</b>
	Trichloroethylene				0	X	0	0
	Triethylamine			~	0	-	-	-
W	Water				0	0	0	0
Х	Xylene		~	~	0	X	0	0
Ζ	Zinc Chloride		$\checkmark$		0	0	X	0

Toxic: Chemicals designated as toxic substances. Hazardous: Chemicals designated as hazardous substances.

Dangerous: Class 4 special flammable substances, Class 1 petroleum substances, alcohols,

and Class 2 petroleum-based materials prone to generating static electricity. Resin N: Resin-made nipples for SHIMETAC. AISI 304 (SUS304): Bolts and nuts for SHIMETAC. AISI 316 (SUS316): Stainless steel holders and Nipple F for SHIMETAC.

Note: The classifications used in this table follow Japanese standards. Please contact us for details.

Symbol Explanations:

0 : No or minimal impact. ♦ : Significant impact (may still be usable under certain conditions).

X : Not suitable for use. - : No data available.



# TOTAKU Food-Grade Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

# **Featured Products**

SD-F	02
SD-HF	03

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

# TOTAKU SD-F



# **Standard Dimensions and Properties**

### Features

- Tasteless and odorless, making it ideal for food transportation.
- Free from phthalate-based plasticizers, meeting the requirements of Japanese Ministry of Health, Labour and Welfare Notification No. 267, effective August 1, 2003.
- Suitable for use with oils and fatty foods.
- Complies with the Standards for Food and Additives (Japanese Ministry of Health Notification No. 370).

# Applications

- Suitable for transporting sake, shochu, beer, and soft drinks.
- Ideal for transporting other food products.
- Effective for non-food oil transportation.
- Designed for both suction and discharge uses

### Cautions

- For transporting food-grade powders, wrap a metal wire (such as copper wire) around the hose's exterior and connect it to a grounding point.
- After use, ensure no high-concentration alcohol or other organic solvents remain inside the hose.

Non Dian	ninal neter	In Diar	ner neter	Ou Diar	uter neter	Refe We	rence ight	Len	gth	Allowable (at room te	Pressure mperature)	Allowable E (to the center of	Bend Radius axis of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.23	31.2	0.23	340	164	50	72.52	0.50	9.45	240
1.25	32	1.26	32.0	1.54	39.2	0.34	510	164	50	65.27	0.45	13.39	340
1.5	38	1.50	38.0	1.81	46.0	0.44	650	164	50	58.02	0.40	13.78	350
2	50	2.00	50.8	2.40	61.0	0.75	1120	164	50	58.02	0.40	19.69	500
2.5	65	2.50	63.5	2.94	74.8	1.02	1525	65/164	20/50	58.02	0.40	23.62	600
3	75	3.00	76.2	3.46	88.0	1.27	1885	65/164	20/50	58.02	0.40	30.51	775
3.5*	90	3.50	88.9	3.96	100.5	1.47	2190	65	20	43.51	0.30	41.93	1065
4	100	4.00	101.6	4.56	115.8	2.07	3080	65	20	43.51	0.30	45.28	1150
5*	125	5.00	127.0	5.55	141.0	2.46	3660	65	20	36.26	0.25	62.99	1600
6*	150	6.00	152.4	6.61	167.8	3.36	5000	65	20	29.01	0.20	74.80	1900

Sizes marked with an asterisk (\*) and all sizes with grounding wires are made-to-order items. For inquiries about order quantities or other details, please contact us directly. Our food hoses comply with the Japanese Food Sanitation Act but do not meet U.S. standards. They are currently under development, so please contact us for more details.

### Operating Temperature Range:

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

#### Specifications and Standards for Food, Food Additives, etc. (Japanese Ministry of Health and Welfare Notification No. 370, 1959)

Japan's Specifications and Standards for Food, Food Additives, etc. were revised under the following notification (excerpt):

Japanese Ministry of Health, Labour and Welfare Notification No. 196, 2020 A positive list system was introduced, allowing only materials that have been evaluated for safety to be used in food-related utensils, containers, and packaging.

- Compliance of Our Products with the Japanese Food Sanitation Act Our food-grade hoses<sup>1</sup> comply with the Japanese Food Sanitation Act<sup>2</sup>.
- Regulatory Standards: Refer to Section Number 3-A-8 Appendix 1 (Positive List) of the "Specifications and Standards for Food, Food Additives, etc." (Japanese Ministry of Health and Welfare Notification No. 370, 1959), established under Article 18 of the Japanese Food Sanitation Act (Act No. 233, 1947).

<sup>1</sup> Food-Grade Hoses: For assistance with selecting hoses suitable for food-related use, please contact us.
<sup>2</sup> Compliance with the Japanese Food Sanitation Act, Our products comply with the requirements of the Japanese National Positive List (PL) or fall under transitional measures. Transitional measures apply to utensils, containers, and packaging confirmed to be equivalent to those distributed before the law's enforcement. These items may continue to be distributed for up to 5 years after enforcement (until May 31, 2025).

#### **About Oils and Fatty Foods**

According to the Japanese Food Sanitation Act, oils and fatty foods are defined as: "Foods or food surfaces containing approximately 20% or more oil or fat, as well as foods that include such oils or fats, excluding dried solid foods." Examples include beef tallow, vegetable oil, ham, bacon, beef, pork, chocolate, potato chips, tempura, deep-fried tofu, fried fish cakes, croquettes, tonkatsu (breaded pork cutlet), mayonnaise, dressing, cheese, butter, hamburg steak, gyoza, fried chicken, meatballs, curry, beef stew, nikujaga (beef and potato stew), stir-fried vegetables, kinpira gobo (braised burdock root), stewed dishes with oil or fried tofu, potato salad, donuts, cakes, cookies, karinto (sweet fried snacks), and fried rice crackers, among others.

# **TOTAKU SD-HF**



# Features

- This is a heat-resistant version of TOTAKU SD-F.
- Excellent heat resistance with a maximum operating temperature of 176°F (80°C).
- Free of phthalate-based plasticizers, compliant with Japanese Ministry of Health, Labour and Welfare Notification No. 267 (effective August 1, 2003).
- Suitable for use with oils and fatty foods. ٠
- Compliant with Japan's Specifications and Standards for Food, Food Additives, Etc. (Japanese Ministry of Health and Welfare Notification No. 370).

# Applications

- Suitable for transporting sake, shochu, beer, and soft drinks.
- Ideal for other food transportation.
- Designed for both suction and discharge use.

# Cautions

٠ After use, ensure that high-concentration alcohol or other organic solvents do not remain inside the hose.

Non Dian	ninal neter	In Dian	ner neter	Οι Diar	uter neter	Refe We	rence ight	Len	gth	Allowable (at room te	e Pressure mperature)	Allowable E (to the center of	Bend Radius axis of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.23	31.2	0.25	370	164	50	29.01	0.20	13.78	350
1.25	32	1.26	32.0	1.54	39.2	0.35	525	164	50	29.01	0.20	19.69	500
1.5	38	1.50	38.0	1.81	46.0	0.48	715	164	50	29.01	0.20	23.62	600
2	50	2.00	50.8	2.40	61.0	0.80	1190	164	50	29.01	0.20	29.53	750
2.5	65	2.50	63.5	2.94	74.8	1.11	1650	65/164	20/50	29.01	0.20	49.21	1250
3	75	3.00	76.2	3.46	88.0	1.36	2020	65/164	20/50	29.01	0.20	66.93	1700

Our food hoses comply with the Japanese Food Sanitation Act but do not meet U.S. standards. They are currently under development, so please contact us for more details.

**Operating Temperature Range:** °F: 86 to 176

# °C: 30 to 80

# Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

# **Standard Dimensions and Properties**



# **TOTAKU Ducting Hoses**

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

# **Featured Products**

DUCT-EE	02	DUCT-AL	12
CLEAR DUCT	03	MD-18	13
DUCT-D	04	MD-25	14
DUCT-FR	05	MD-45	15
HERAN DUCT	06	IT-13	16
BELLOWS DUCT	07		
DUCT-AROR	08		
DUCT-OR	09		
DUCT-PP	10		
RETRACTABLE DU	CT 11		An

#### Notice:

- The data in this catalog uses values in a straight hose configuration. (The allowable Vacuum Pressure for duct hoses is measured when the hose is in a straight configuration with both ends fixed.)
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

# TOTAKU DUCT-EE





# Standard Dimensions and Properties

#### Features

- This is a standard type of TOTAKU DUCT-D.
- Compared to TOTAKU DUCT-D, it has lower internal resistance, allowing for greater transport capacity.
- It is flexible and lightweight, reducing labor during handling and installation.
- Easy to cut and install, simplifying ductwork.

## Applications

- / Useful for indoor air supply and exhaust.
- Ideal for air supply and exhaust in factory equipment.
- Effective for dust collection and other air supply/exhaust needs.
- Suitable for drainage purposes (for surface-level drainage).

#### **Compatibility Chart for Steel and PVC Pipes**

Hose N Dian	ominal neter			Арј	olicable	Pipe T	ype			
		Α	STM:A5	3 Туре	F	JP s (AS	standar <i>TM:D178</i>	rd PVC p Sequival	oipe ent)	SY Band Product
inch	mm	Nom Diam	inal eter	Ou Dian	iter neter	Non Dian	ninal neter	Ou Diam	ter leter	Number
		inch	mm	inch	mm	inch	mm	inch	mm	
3	75	2.56	65	3.00	76.3	2.6	65	2.99	76	SY75
3.5	90	3.15	80	3.51	89.1	3.0	75	3.50	89	SY90
4	100	3.54	90	4.00	101.6	-	-	-	-	SY100
4.5	115	3.94	100	4.50	114.3	3.9	100	4.49	114	SY117
6.5	165	5.91	150	6.50	165.2	5.9	150	6.50	165	SY165

For installation, insert directly and secure with an SY band.

Non Dian	ninal neter	In Diar	ner neter	Ou Diam	ter neter	Pi	tch	Refer Wei	rence ght	Len	gth	Allowab (at room	le Pre temper	ssure ature)	Allowal Pr (at room	ole Vaci essure <i>temperc</i>	uum ature)	Allowable (to the of t	e Bend center the hose	Radius axis
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi		MPa	inHg	k	Pa	inch		mm
1.25	32	1.28	32.4	1.52	38.6	0.33	8.4	0.15	220	164	50	8.70		0.06	-19.49	-6	6.00	1.26		32
1.5	38	1.47	37.3	1.75	44.5	0.36	9.2	0.20	295	164	50	8.70		0.06	-19.49	-6	6.00	1.50		38
2	50	1.99	50.6	2.37	60.2	0.39	10.0	0.39	585	98	30	7.25		0.05	-19.49	-6	6.00	1.97		50
2.5	65	2.46	62.4	2.83	72.0	0.47	12.0	0.43	645	98	30	5.80		0.04	-19.49	-6	6.00	2.56		65
3*	75	3.01	76.4	3.40	86.4	0.51	13.0	0.52	775	98	30	5.80		0.04	-9.74	-3	3.00	2.95		75
3.5*	90	3.50	88.9	3.92	99.5	0.53	13.5	0.64	945	98	30	4.35		0.03	-9.74	-3	3.00	3.54		90
4*	100	4.00	101.6	4.42	112.2	0.59	15.0	0.69	1020	98	30	4.35		0.03	-6.35	-2	1.50	3.94		100
4.5*	115	4.50	114.3	4.96	125.9	0.69	17.4	0.84	1255	98	20	4.35		0.03	-6.35	-2	0.00	4.33		110
5	125	4.96	125.9	5.46	138.7	0.83	21.0	0.91	1350	65	20	2.90		0.02	-5.91	-2	0.00	4.92		125
6	150	6.00	152.4	6.49	164.8	0.79	20.0	1.12	1670	65	20	2.90		0.02	-4.28	-14	4.50	5.91		150
6.5*	165	6.50	165.0	7.00	177.8	0.87	22.0	1.19	1770	65	20	2.90		0.02	-2.95	-10	0.00	5.91		150
7	175	7.00	177.8	7.50	190.6	0.79	20.0	1.30	1935	65	20	2.90		0.02	-2.95	-1	0.00	6.89		175
8	200	8.02	203.7	8.55	217.1	0.89	22.5	1.47	2190	65	20	1.45		0.01	-1.77	-6	5.00	7.87		200
9	225	8.94	227.0	9.46	240.4	0.93	23.5	1.64	2440	32	10	1.45		0.01	-1.62	-5	5.50	8.86		225
10	250	9.92	252.0	10.48	266.2	0.98	25.0	1.98	2950	32	10	1.45		0.01	-1.33	-4	1.50	9.84		250
11	275	10.94	278.0	11.52	292.6	1.10	28.0	2.12	3150	32	10	1.45		0.01	-1.18	-4	1.00	10.83		275
12	300	11.93	303.0	12.52	318.0	1.18	30.0	2.34	3480	32	10	1.45		0.01	-0.89	-3	3.00	11.81		300
Sizes n	narked	with an	asterisk (	*) can be	directly	connec	ted to s	steel pip	es.											
Sizo	in	ch	1.25	1.5	2	2.5	3	3.	.5	4	4.5	5	6	6.5	7	8	9	10	11	12
Size	m	m	32	38	50	65	75	9	0	100	115	125	150	165	175	200	225	250	275	300
Cuff	Availa	ble	Yes	Yes	Yes	Yes	Yes	s Ye	es '	Yes	No	Yes	Yes	No	Yes	Yes	No	No	No	No
		1 1 47					1.11					c /								

Note: The 7-inch ( $\varphi$ 175) diameter cuff is made of EPDM, while other sizes are made of soft PVC.

### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

# Notes:

• The permissible pressure varies with operating temperature.

02 of 16 | TOTAKU Ducting Hoses

# TOTAKU CLEAR DUCT

Part Number - 21121





#### Features

• A transparent type of TOTAKU DUCT-EE, allowing for visual inspection of transported materials

#### Applications

- Suitable for dust collection in woodworking machinery.
- Ideal for the transport of powders, granules, and gases.
- Useful for air supply and exhaust in indoor and factory equipment.
- Effective when visual inspection of transported materials is required.
- Suitable for drainage applications (for surface-level drainage).

Non Dian	ninal neter	In Diar	ner neter	Oı Diar	uter neter	Pi	tch	Refer Wei	ence ght	Len	gth	Allowable P (at room temp	ressure perature)	Allowable Press (at room ten	Vacuum ure aperature)	Allowable Ben (to the cente) of the hos	d Radius r axis se)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.25	32	1.28	32.4	1.52	38.6	0.33	8.4	0.15	220	164	50	8.70	0.06	-19.49	-66.00	1.26	32
1.5	38	1.47	37.3	1.75	44.5	0.36	9.2	0.20	295	164	50	8.70	0.06	-19.49	-66.00	1.50	38
2	50	1.99	50.6	2.37	60.2	0.39	10.0	0.39	585	98	30	7.25	0.05	-19.49	-66.00	1.97	50
2.5	65	2.46	62.4	2.83	72.0	0.47	12.0	0.43	645	98	30	5.80	0.04	-19.49	-66.00	2.56	65
3	75	3.01	76.4	3.40	86.4	0.51	13.0	0.51	755	98	30	5.80	0.04	-9.74	-33.00	2.95	75
3.5	90	3.50	88.9	3.92	99.5	0.53	13.5	0.64	950	98	30	4.35	0.03	-9.74	-33.00	3.54	90
4	100	4.00	101.6	4.42	112.2	0.59	15.0	0.69	1020	98	30	4.35	0.03	-6.35	-21.50	3.94	100
5	125	4.96	125.9	5.46	138.7	0.83	21.0	0.91	1350	65	20	2.90	0.02	-5.91	-20.00	4.92	125
6	150	6.00	152.4	6.49	164.8	0.79	20.0	1.12	1670	65	20	2.90	0.02	-4.28	-14.50	5.91	150
8	200	8.02	203.7	8.55	217.1	0.89	22.5	1.47	2190	65	20	1.45	0.01	-1.77	-6.00	7.87	200

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. Cuffs: Made of soft PVC.

#### Operating Temperature Range:

# Notes:

°F: 14 to 122 °C: -10 to 50

# TOTAKU DUCT-D



#### Features

- Lightweight and flexible, improving handling and installation efficiency.
- Easy to cut and install, simplifying ductwork.

## Applications

- Suitable for air supply and exhaust in equipment and machinery.
- Ideal for air ventilation systems.
- Effective for dust collection, air supply, and exhaust applications.
- Suitable for drainage purposes (for surface-level drainage).

## **Standard Dimensions and Properties**

Non Dian	ninal neter	In Diar	ner neter	Ou Dian	iter neter	Pit	ch	Refei Wei	rence ight	Len	gth	Allowable (at room ter	Pressure mperature)	Allowable Press (at room ten	Vacuum aure aperature)	Allowable Be (to the cen of the h	nd Radius ter axis ose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.25	32	1.28	32.4	1.52	38.6	0.30	7.5	0.17	255	164	50	8.70	0.06	-19.49	-66.00	1.26	32
1.5	38	1.47	37.3	1.75	44.5	0.31	7.9	0.24	360	164	50	8.70	0.06	-19.49	-66.00	1.50	38
2	50	2.00	50.8	2.35	59.8	0.43	11.0	0.37	545	164	50	7.25	0.05	-19.49	-66.00	1.97	50
2.5	65	2.52	64.0	2.88	73.2	0.44	11.1	0.46	685	98	30	5.80	0.04	-19.49	-66.00	2.56	65
3*	75	3.01	76.5	3.38	85.9	0.46	11.7	0.55	825	98	30	5.80	0.04	-9.74	-33.00	2.95	75
3.5*	90	3.54	90.0	3.94	100.0	0.47	12.0	0.71	1050	98	30	4.35	0.03	-9.74	-33.00	3.54	90
4*	100	4.06	103.0	4.45	113.0	0.47	12.0	0.84	1245	98	30	4.35	0.03	-6.64	-22.50	3.94	100
5	125	5.01	127.3	5.41	137.3	0.48	12.1	0.97	1445	65	20	2.90	0.02	-3.54	-12.00	4.92	125
6	150	5.96	151.4	6.38	162.0	0.53	13.5	1.23	1830	65	20	2.90	0.02	-2.95	-10.00	5.91	150
7	175	6.95	176.6	7.39	187.8	0.54	13.7	1.46	2170	65	20	1.45	0.01	-2.36	-8.00	6.89	175
8	200	8.07	205.0	8.54	216.8	0.56	14.3	1.85	2760	65	20	1.45	0.01	-1.92	-6.50	7.87	200
10	250	9.93	252.1	10.39	263.9	0.55	13.9	2.21	3290	32	10	1.45	0.01	-1.18	-4.00	9.84	250
12	300	11.93	303.0	12.44	316.0	0.62	15.7	2.75	4090	32	10	1.45	0.01	-0.74	-2.50	11.81	300

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. Note: The 7-inch (φ175 mm) cuff is made of EPDM, while other sizes are made of soft PVC.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

# TOTAKU DUCT-FR



#### Features

- Features a reinforcing cord for superior tensile strength and outstanding flexibility and bending durability.
- The ivory-white color transforms the look of traditional vinyl ducts, blending well with modern equipment.

## Applications

- Suitable for air supply and exhaust in equipment and machinery.
- Ideal for air ventilation systems.
- Effective for dust collection, air supply, and exhaust applications.
- Suitable for drainage purposes (for surface-level drainage).

|--|

Non Dian	ninal neter	In Diar	ner neter	Oı Diar	uter neter	Pi	tch	Refer Wei	ence ght	Len	gth	Allowable (at room ter	Pressure nperature)	Allowable Press (at room ter	Vacuum sure mperature)	Allowable E (to the ce of the	Send Radius enter axis hose)	Fitting (Cuff) Available
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm	Yes/No
1.25	32	1.26	32.0	1.57	40.0	0.33	8.5	0.20	300	164	50	14.50	0.10	-14.47	-49.00	1.26	32	Yes
1.5	38	1.50	38.0	1.82	46.2	0.35	9.0	0.27	400	164	50	14.50	0.10	-14.47	-49.00	1.50	38	Yes
2	50	1.99	50.6	2.40	61.0	0.39	10.0	0.45	665	98	30	11.60	0.08	-14.47	-49.00	1.97	50	Yes
2.5	65	2.46	62.4	2.86	72.6	0.47	12.0	0.49	730	98	30	10.15	0.07	-14.47	-49.00	2.56	65	Yes
3*	75	3.01	76.4	3.42	86.8	0.59	15.1	0.53	795	98	30	10.15	0.07	-11.81	-40.00	2.95	75	Yes
3.5*	90	3.50	88.9	3.91	99.3	0.59	15.1	0.64	950	98	30	10.15	0.07	-8.56	-29.00	3.54	90	Yes
4*	100	4.00	101.6	4.45	113.0	0.65	16.4	0.76	1135	98	30	10.15	0.07	-6.35	-21.50	3.94	100	Yes
5	125	4.96	125.9	5.48	139.3	0.83	21.0	1.10	1640	65	20	5.80	0.04	-5.91	-20.00	4.92	125	Yes
6	150	6.00	152.4	6.54	166.0	0.79	20.0	1.34	2000	65	20	4.35	0.03	-5.91	-20.00	5.91	150	Yes
8	200	8.02	203.7	8.56	217.5	0.89	22.5	1.85	2760	65	20	2.90	0.02	-3.25	-11.00	7.87	200	Yes

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. Cuffs: Made of soft PVC.

Notes:

# **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

# TOTAKU HERAN DUCT

Part Number - 21108





# **Standard Dimensions and Properties**

## Features

- Offers more than twice the abrasion resistance compared to our PVC ducts.
- Superior resistance to cold and heat.
   (Operating temperature range: -22°F to 176°F / -30°C to 80°C).
- An anti-static duct hose with excellent static prevention properties. (Material volume resistivity:  $3,937 \Omega \cdot in (10^5 \Omega \cdot cm)$  or less)
- Highly resistant to ozone cracking, unlike conventional rubber hoses.

# Applications

- Suitable for transporting powders, granules, iron powder, paper scraps, and wood dust.
- Ideal for high-temperature air blowers.
- Effective for duct hose applications requiring abrasion resistance, heat resistance, and conductivity.
- Suitable for drainage purposes (for surface-level drainage).

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Pi	tch	Refei Wei	rence ight	Len	gth	Allowable (at room ter	Pressure mperature)	Allowable Press (at room ter	Vacuum sure mperature)	Allowable Be (to the cer) of the l	end Radius hter axis hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.5	38	1.50	38.0	1.84	46.8	0.37	9.5	0.23	335	98	30	4.35	0.030	-11.81	-40.00	1.77	45
2	50	1.99	50.6	2.41	61.2	0.39	10.0	0.37	550	98	30	4.35	0.030	-11.81	-40.00	2.17	55
2.5	65	2.46	62.4	2.87	73.0	0.47	12.0	0.41	605	98	30	2.90	0.020	-9.74	-33.00	2.56	65
3	75	3.01	76.4	3.43	87.2	0.51	13.0	0.49	725	98	30	2.90	0.020	-7.83	-26.50	2.95	75
3.5	90	3.50	88.9	3.95	100.3	0.53	13.5	0.60	890	98	30	1.45	0.010	-5.91	-20.00	3.54	90
4	100	4.00	101.6	4.45	113.0	0.59	15.0	0.63	935	98	30	1.45	0.010	-5.91	-20.00	3.94	100
5	125	4.96	125.9	5.50	139.7	0.85	21.5	0.88	1315	65	20	1.45	0.010	-4.87	-16.50	4.92	125
6	150	6.00	152.4	6.54	166.2	0.79	20.0	1.05	1560	65	20	1.45	0.010	-3.84	-13.00	5.91	150
8	200	8.02	203.7	8.56	217.5	0.89	22.5	1.39	2070	65	20	0.73	0.005	-3.84	-13.00	7.87	200
10	250	9.92	252.0	10.80	274.2	0.98	25.0	3.78	5620	32	10	0.73	0.005	-4.87	-16.50	13.78	350
12	300	11.93	303.0	12.92	328.2	1.18	30.0	4.13	6150	32	10	0.73	0.005	-4.87	-16.50	13.78	350

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. Dedicated EPDM cuffs are available (1.5 inches to 8 inches / φ38 mm to φ200 mm).

# **Operating Temperature Range:**

°F: -22 to 176 °C: -30 to 80

### Notes:

 The permissible pressure varies with operating temperature.

Scan, tap, or touch for product videos



# TOTAKU BELLOWS DUCT

Part Number - 21104





**Standard Dimensions and Properties** 

#### Features

- Can be expanded and contracted freely, allowing for storage at approximately one-third of its size.
- Lightweight despite its large diameter, making it easy to transport.

## Applications

- Ideal for air supply and exhaust in manhole and tunnel construction work.
- Effective for air supply, exhaust, and dust collection in various / fields.
- Suitable for drainage purposes (for surface-level drainage).

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Pit	tch	Refer Wei	ence ght	Leng	gth	Allowable (at room ter	Pressure nperature)	Allowable Pressi (at room tem	/acuum ure perature)	Allowable Ben (to the cente) of the ho	d Radius er axis se)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
14	350	13.78	350.0	14.45	367.0	1.97	50.0	2.71	4040	32	10	0.73	0.005	-0.40	-1.35	13.78	350
16	400	15.75	400.0	16.46	418.0	2.36	60.0	3.27	4860	32	10	0.58	0.004	-0.28	-0.95	15.75	400
18	450	17.72	450.0	18.46	469.0	2.36	60.0	3.71	5520	32	10	0.58	0.004	-0.28	-0.95	17.72	450
20	500	19.69	500.0	20.47	520.0	2.36	60.0	4.15	6180	32	10	0.44	0.003	-0.28	-0.95	19.69	500
22*	550	21.65	550.0	22.44	570.0	2.36	60.0	4.87	7250	32	10	0.44	0.003	-0.21	-0.70	21.65	550

\* This is a made-to-order product. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

# Notes:

# TOTAKU DUCT-AROR

Part Number - 21186





# **Standard Dimensions and Properties**

# Features

- Offers excellent abrasion and oil resistance.
- In addition to abrasion resistance, it also offers superior anti-static properties (Material volume resistivity: 100,000  $\Omega$ ·in / 10<sup>5</sup>  $\Omega$ ·cm or less)

# Applications

- Ideal for transporting waste oil and scrap materials from metal processing.
- Suitable for use in dust collection systems.
- Effective for recovering gasoline vapor.
- Useful for transporting industrial waste containing oil.
- Appropriate for transporting grains and animal feed.

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Pit	tch	Refer Wei	ence ght	Leng	gth	Allowable (at room ten	Pressure nperature)	Allowable Press (at room ten	Vacuum ure nperature)	Allowable Bo (to the cent) of the c	end Radius nter axis hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.5	38	1.50	38.0	1.85	47.1	0.37	9.5	0.31	460	98	30	14.50	0.10	-19.49	-66.00	1.50	38
2	50	2.00	50.8	2.38	60.4	0.41	10.5	0.40	590	98	30	10.15	0.07	-19.49	-66.00	1.97	50
2.5	65	2.52	64.0	2.89	73.5	0.58	14.8	0.51	760	65	20	7.25	0.05	-19.49	-66.00	2.56	65
3*	75	3.01	76.4	3.44	87.4	0.59	15.1	0.65	960	98	30	7.25	0.05	-9.74	-33.00	2.95	75
4*	100	4.00	101.6	4.50	114.2	0.65	16.4	0.97	1440	65	20	4.35	0.03	-9.74	-33.00	3.94	100

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

# Operating Temperature Range:

°F: -14 to 122 °C: -10 to 50













# TOTAKU DUCT-OR



## Features

- Excellent oil resistance.
- Matches equipment with its ivory color.
- Lightweight with superior bending durability.
- Low internal resistance, contributing to efficient and energy-saving operations.

# Applications

- Useful for the intake and exhaust of oil mist.
- Effective for recovering oil mist from lathes, milling machines, and similar equipment.
- Suitable for drainage purposes (for surface-level drainage).

Standard Dimensions and Prop	perties
------------------------------	---------

Nom Diam	ninal neter	In Dian	ner neter	Ou Diar	uter neter	Pi	tch	Refe We	rence ight	Len	gth	Allowable (at room te	Pressure mperature)	Allowable Pres (at room te	e Vacuum sure mperature)	Allowable I (to the c of the	Bend Radius enter axis e hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
2	50	1.99	50.6	2.37	60.2	0.39	10.0	0.42	625	98	30	7.25	0.05	-19.49	-66.00	1.97	50
3*	75	3.01	76.4	3.40	86.4	0.51	13.0	0.52	775	98	30	5.80	0.04	-9.74	-33.00	2.95	75
4*	100	4.00	101.6	4.42	112.2	0.59	15.0	0.75	1120	98	30	4.35	0.03	-6.35	-21.50	3.94	100
5	125	4.96	125.9	5.46	138.7	0.83	21.0	0.91	1350	65	20	2.90	0.02	-5.91	-20.00	4.92	125
6	150	6.00	152.4	6.49	164.8	0.79	20.0	1.12	1670	65	20	2.90	0.02	-4.28	-14.50	5.91	150
8	200	8.00	203.2	8.52	216.5	0.89	22.5	1.47	2190	65	20	1.45	0.01	-1.77	-6.00	7.87	200

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

# **Oil Resistance (Changes in Flexibility After Oil Immersion)**

# **TOTAKU Oil-Resistant Duct**



No change in flexibility even after immersion in oil for one week. (Kerosene was used in this test.)

### **Generic PVC Duct**



General PVC duct becomes hardened and is unable to withstand bending after oil immersion.

# Operating Temperature Range:

°F: -14 to 122 °C: -10 to 50

# Notes:

• The permissible pressure varies with operating temperature.

09 of 16 | TOTAKU Ducting Hoses

# TOTAKU RIGID DUCT-PP



# **Standard Dimensions and Properties**

### Features

- Achieves a 10-20% weight reduction compared to traditional PVC products.
- Can be freely bent and retains its shape after bending. (Indoor use only. Note: Shape retention decreases as temperature rises.)
- Diameter can be adjusted by twisting the end.
- Easily cut with a knife.
- Ducts can be quickly connected by twisting the ends together.
   (Wrap the joint with vinyl tape or similar material after connection.)
- Can be incinerated after use.

# Applications

- Suitable for spot coolers.
- Effective for air ventilation supply and exhaust.
- Useful for dust collection in woodworking and metal polishing machinery.
- Appropriate for civil engineering, electrical conduit, agricultural, and other uses

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch (when expanded)		Reference Weight		Length		Percentage Change in Diameter		Expansion- Contraction Ratio	Allowable Bend Radius (to the center axis of the hose)		Maximum Operating Temperature	
incl	n mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	Expansion	Contraction	-	inch	mm	°F	°C
2	55	2.17	55.0	2.39	60.8	0.28	7.0	0.30	450	32	10	20	15	1.5	5.51	140	176	80
2.5	65	2.56	65.0	2.79	70.8	0.28	7.0	0.34	510	32	10	20	15	1.5	6.10	155	176	80
3	75	2.95	75.0	3.24	82.4	0.30	7.5	0.45	675	32	10	20	15	1.5	6.89	175	176	80
3.5	90	3.54	90.0	3.83	97.4	0.30	7.5	0.52	775	32	10	20	15	1.5	8.27	210	176	80
4	100	3.94	100.0	4.23	107.4	0.30	7.5	0.57	845	32	10	20	15	1.5	9.06	230	176	80
5	125	4.92	125.0	5.23	132.8	0.30	7.5	0.79	1175	32	10	20	15	1.5	11.81	300	167	75
6	150	5.91	150.0	6.21	157.8	0.30	7.5	0.93	1380	32	10	20	15	1.5	13.78	350	167	75
7	175	6.89	175.0	7.20	182.8	0.30	7.5	1.20	1785	32	10	20	15	1.5	15.75	400	167	75
8	200	7.87	200.0	8.19	208.0	0.30	7.5	1.25	1855	32	10	20	15	1.5	17.72	450	167	75
10	250	9.84	250.0	10.22	259.6	0.41	10.5	2.15	3195	13	4	15	10	1.5	37.80	960	158	70
12	300	11.81	300.0	12.19	309.6	0.41	10.5	2.68	3990	13	4	15	10	1.5	39.37	1000	158	70

Note: This is the length in the contracted state.

End covers are available in all sizes.

# Operating Temperature Range:

°F: 14 to 176 °C: -10 to 80

# Notes:

 The permissible pressure varies with operating temperature.

Scan, tap, or touch for product videos


Can expand and contract freely, with the ability to be fixed at any angle or direction. (Note: Shape retention may decrease for larger

Reduces to 1/3 to 1/4 of its original length, facilitating easier transport and minimizing storage space before installation.

Suitable for hot air (below 176°F / 80°C) supply and exhaust.

Effective for equipment exhaust and similar applications.

Ideal for air conditioning and ventilation use.

### TOTAKU RETRACTABLE DUCT

Features

•

•

.

diameters.)

Applications



### Standard Dimensions and Properties

#### Pitch Maximum Nominal Inner Outer Reference Cyclic Bend Cycle Allowable Bend Radius (when Length Operating Diameter Diameter Weight Durability Strength Diameter (to the center axis of the hose) Temperature expanded) °F °C inch mm inch mm inch mm inch mm lbs/ft g/m feet m inch mm 38 1.38 35 1.65 42.0 0.41 10.5 0.11 5 1.18 30 176 80 1.5 165 16 40 50 1.97 2.28 58.0 0.13 190 5 1.57 176 80 2 50 0.48 12.3 16 2.83 2.5 0.15 2.17 55 65 2.48 63 72.0 0.55 14.0 230 5 176 80 16 Over Over 100,000 75 2.80 71 0.17 255 5 2.36 60 176 80 3 3.19 81.0 0.62 15.7 16 100,000 cycles 70 176 90 83 0.62 15.7 0.25 5 (left and 2.76 80 3.5 3.27 3.70 94.0 365 16 cycles (32°F/0°C, right 90°) 100 3.82 97 108.0 0.30 80 176 4.25 0.67 17.0 440 5 3.15 80 4 16 77°F/25°C) (32°F/0°C, 77°F/25°C) 5 125 4.84 123 5 3.94 100 5.31 135.0 0.73 18.5 0.42 630 176 80 16 5.71 5 4.72 120 150 145 6.22 158.0 0.89 22.5 0.49 730 176 80 6 16 8 200 7.72 196 8.25 209.5 0.96 24.5 0.62 920 16 5 6.30 160 176 80 12.19 309.5 1.06 27.0 5 9.45 240 12 300 11.57 294 1.04 1555 16 176 80

Note: This product is sold in standard lengths (with cuffs on both ends).

#### **Operating Temperature Range:**

#### Notes:

°F: -4 to 176 °C: -20 to 80

20 to 80

• The permissible pressure varies with operating temperature.

### TOTAKU DUCT-AL

Part Number - 21102





#### **Standard Dimensions and Properties**

#### Features

- Offers flexibility and expandability, making installation in tight spaces easier.
- Can compress to 1/5 of its original length, allowing for compact storage and saving on inventory space.
- Resists repeated bending and provides excellent heat resistance (up to 176°F / 80°C).

#### Applications

- Suitable for ducting ventilation fans in residential, apartment, and commercial settings.
- Ideal for air conditioning and ventilation in buildings such as offices and commercial properties.

#### Notes

- This material is not non-combustible and should not be used for range hood exhaust systems.
- Continuous operating temperature range: -4°F to 176°F (-20°C to 80°C).

Nor Diar	ninal neter	Inr Diam	ner neter	Ou Dian	iter neter	Pi (wi expa	tch hen nded)	Refei Wei	rence ight	Leng	gth	Allov Pres (at room te	vable sure mperature)	Allowable Pres (at room te	e Vacuum sure mperature)	Allowable (to the ce the	Bend Radius enter axis of hose)	Maxin Opera Temper	num ating rature
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm	°F	°C
1.5	38	1.54	39	1.77	45.0	0.43	10.8	0.08	125	16	5	2.90	0.020	-9.74	-33.00	1.18	30	176	80
2	50	1.97	50	2.18	55.3	0.43	10.8	0.11	160	16	5	2.90	0.020	-9.74	-33.00	1.38	35	176	80
2.5	65	2.52	64	2.77	70.3	0.43	10.8	0.13	195	16	5	2.90	0.020	-9.74	-33.00	1.77	45	176	80
3	75	2.95	75	3.16	80.3	0.43	10.8	0.16	235	16	5	1.45	0.010	-7.83	-26.50	2.17	55	176	80
4	100	3.86	98	4.15	105.3	0.43	10.8	0.20	300	16	5	1.45	0.010	-4.87	-16.50	2.76	70	176	80
4.5	117	4.45	113	4.70	119.3	0.43	10.8	0.24	360	16	5	1.45	0.010	-3.84	-13.00	2.95	75	176	80
5	125	4.92	125	5.13	130.3	0.43	10.8	0.25	375	16	5	1.45	0.010	-2.95	-10.00	3.54	90	176	80
6	150	5.91	150	6.13	155.7	0.43	10.8	0.39	580	16	5	1.45	0.010	-2.95	-10.00	4.13	105	176	80
7	175	6.89	175	7.11	180.7	0.43	10.8	0.45	670	16	5	1.45	0.010	-2.95	-10.00	4.72	120	176	80
8	200	7.87	200	8.10	205.7	0.43	10.8	0.53	785	16	5	1.45	0.010	-1.92	-6.50	5.91	150	176	80
10	250	9.84	250	10.07	255.9	0.43	10.8	0.77	1150	16	5	1.16	0.008	-1.92	-6.50	7.28	185	176	80
12	300	11.81	300	12.04	305.9	0.43	10.8	0.90	1345	16	5	1.02	0.007	-1.18	-4.00	9.06	230	176	80

Notes: The inner diameter is a reference value. When using commercially available insert-type fittings, please verify with the actual product. When inserting nipples or similar components, ensure that the hose is in an expanded state.

#### **TOTAKU DUCT-AL Components**

Adapter Fitting (Material: PE) *Part Number 92101* A reducer fitting designed to easily connect TOTAKU DUCT-AL to the duct connection port of ventilation fans.



Nominal I	Diameter		4	E	3	0	2	[	)
inch	mm	inch	mm	inch	mm	inch	mm	inch	mm
100	4	3.94	100	3.86	98	4.37	111	4.57	116
150	6	5.91	150	5.83	148	6.34	161	6.54	166
200	8	7.87	200	7.80	198	8.31	211	8.50	216

Operating Temperature Range:

Duct Connector (Material: PE) *Part Number 92102* A same-diameter connector used for joining sections of TOTAKU DUCT-AL.



Nominal D	iameter	A	۱.	E	3
inch	mm	inch	mm	inch	mm
100	4	3.94	100	3.86	98
150	6	5.91	150	5.83	148
200	8	7.87	200	7.80	198





For installation, use either the Spiral Wire Band or the ABA Band. Note: Available in a range of sizes.

#### Notes:

• The permissible pressure varies with operating temperature.

°F: -4 to 176 °C: -20 to 80 12 of 16 | TOTAKU Ducting Hoses

### **TOTAKU MD-18**

Part Number - 21114





**Standard Dimensions and Properties** 

#### Features

- Made with aluminum foil, glass cloth, and a reinforced core of galvanized steel sheet, suitable for use at temperatures up to 356°F (180°C).
- Fully flexible and easy to expand and contract, simplifying storage, handling, and transport. (Repeated expansion and contraction should be avoided.)
- Uses an aluminum-glass cloth sheet with superior flame-retardant properties. (Certified as Class 1 flame-resistant.)

#### Applications

• Ideal for air ventilation systems and intake/exhaust in hot air circulation devices.

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	uter neter	Refei Wei	rence ight	Len	gth	Allowable (at room te	Pressure mperature)	Allowable Pres (at room te	e Vacuum sure mperature)	Allowable Be (to the center axi	nd Radius s of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
2	50	2.01	51.0	2.15	54.5	0.27	405	16	5	1.02	0.007	-2.51	-8.5	4.33	110
2.5	65	2.66	67.5	2.81	71.5	0.35	520	16	5	1.02	0.007	-2.36	-8.0	5.51	140
3	75	2.99	76.0	3.15	80.0	0.39	580	16	5	1.02	0.007	-2.07	-7.0	6.30	160
3.5	90	3.58	91.0	3.74	95.0	0.42	630	16	5	1.02	0.007	-2.07	-7.0	7.48	190
4	100	4.04	102.5	4.17	106.0	0.48	720	16	5	1.02	0.007	-1.92	-6.5	8.27	210
5	125	5.02	127.5	5.16	131.0	0.58	860	16	5	1.02	0.007	-1.92	-6.5	9.84	250
6	150	5.98	152.0	6.12	155.5	0.71	1050	16	5	1.02	0.007	-1.77	-6.0	11.02	280
7	175	6.95	176.5	7.09	180.0	0.80	1185	16	5	1.02	0.007	-1.48	-5.0	13.39	340
8	200	7.95	202.0	8.07	205.0	0.94	1400	16	5	1.02	0.007	-1.33	-4.5	14.96	380
10	250	9.96	253.0	10.08	256.0	1.20	1780	16	5	1.02	0.007	-0.89	-3.0	20.08	510
12	300	11.93	303.0	12.07	306.5	1.41	2100	16	5	1.02	0.007	-0.89	-3.0	24.02	610
Repeate	ed bend	ina and e	expansion	n is not re	commen	ded.									

#### **Operating Temperature Range:**

°F: -4 to 356 °C: -20 to 180

#### Notes:

• The permissible pressure varies with operating temperature.



### **TOTAKU MD-25**

Part Number - 21115





**Standard Dimensions and Properties** 

#### Features

- Certified as non-combustible by the Japanese Minister of Land, Infrastructure, Transport and Tourism (Certification No. NM-5255).
- Made with specially coated glass cloth and a reinforced core of stainless steel (SUS304), suitable for use at temperatures up to 482°F (250°C).
- ۲ Freely expandable and contractible, making it easy to store, handle, and transport.
- /The specially coated glass cloth used offers excellent flameretardant properties (Certified as Class 1 flame-resistant).

#### **Applications**

Suitable for hot air circulation devices and as suction ducts for welding sparks.

Non Dian	ninal neter	In Dian	ner neter	Οι Diar	iter neter	Refer Wei	rence ight	Len	gth	Allowable (at room ter	Pressure mperature)	Allowable Pres (at room te	e Vacuum sure mperature)	Allowable Ber (to the center axis	nd Radius s of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
2	50	2.01	51.0	2.15	54.5	0.24	360	16	5	1.02	0.007	-2.51	-8.5	4.33	110
2.5	65	2.64	67.0	2.81	71.5	0.32	480	16	5	1.02	0.007	-2.36	-8.0	5.51	140
3	75	2.99	76.0	3.15	80.0	0.35	525	16	5	1.02	0.007	-2.07	-7.0	6.30	160
3.5	90	3.58	91.0	3.72	94.5	0.37	545	16	5	1.02	0.007	-1.92	-6.5	7.48	190
4	100	4.04	102.5	4.17	106.0	0.43	635	16	5	1.02	0.007	-1.92	-6.5	8.27	210
5	125	5.02	127.5	5.16	131.0	0.52	770	16	5	1.02	0.007	-1.77	-6.0	9.84	250
6	150	6.00	152.5	6.12	155.5	0.61	910	16	5	1.02	0.007	-1.18	-4.0	11.02	280
7	175	6.95	176.5	7.09	180.0	0.78	1165	16	5	1.02	0.007	-1.18	-4.0	13.39	340
8	200	7.95	202.0	8.07	205.0	0.83	1240	16	5	1.02	0.007	-0.89	-3.0	14.96	380
10	250	9.96	253.0	10.08	256.0	1.06	1570	16	5	1.02	0.007	-0.89	-3.0	20.08	510
12	300	11.95	303.5	12.07	306.5	1.28	1905	16	5	1.02	0.007	-0.89	-3.0	24.02	610
Reneate	ed hend	ina and e	exnansion	n is not re	comment	ded									

#### **Operating Temperature Range:**

°F: -4 to 482 °C: -20 to 250

#### Notes:

 The permissible pressure varies with operating temperature.



### **TOTAKU MD-45**

Part Number - 21116





**Standard Dimensions and Properties** 

#### Features

- Made entirely of stainless steel (SUS304) with excellent heat resistance, suitable for use at temperatures up to 842°F (450°C).
- Resistant to corrosion from gases containing acids, alkalis, and solvents at room temperature.
- Designed for fixed ducting but can be shaped to include bends. (Not suitable for repeated bending.)

Non Dian	ninal neter	In Dian	ner neter	Οι Dian	ıter neter	Refei Wei	rence ight	Len	gth	Allowable (at room te	Pressure mperature)	Allowabl Pres (at room t	e Vacuum ssure emperature)	Allowable Be (to the center ax	end Radius is of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
2	50	2.07	52.5	2.20	56.0	0.25	365	6	2	1.02	0.007	-3.10	-10.5	6.69	170
2.5	65	2.64	67.0	2.81	71.5	0.31	460	6	2	1.02	0.007	-2.95	-10.0	8.27	210
3	75	2.99	76.0	3.15	80.0	0.35	525	6	2	1.02	0.007	-2.95	-10.0	9.45	240
3.5	90	3.60	91.5	3.74	95.0	0.38	570	6	2	1.02	0.007	-2.66	-9.0	11.42	290
4	100	4.04	102.5	4.17	106.0	0.43	635	6	2	1.02	0.007	-2.36	-8.0	12.60	320
5	125	5.02	127.5	5.16	131.0	0.52	780	6	2	1.02	0.007	-2.07	-7.0	14.96	380
6	150	6.00	152.5	6.10	155.0	0.62	930	6	2	1.02	0.007	-1.92	-6.5	16.54	420
7	175	6.95	176.5	7.09	180.0	0.69	1030	6	2	1.02	0.007	-1.92	-6.5	20.08	510
8	200	7.95	202.0	8.07	205.0	0.83	1240	6	2	1.02	0.007	-1.77	-6.0	22.44	570
10	250	9.96	253.0	10.08	256.0	1.06	1570	6	2	1.02	0.007	-1.33	-4.5	30.31	770
12	300	11.95	303.5	12.07	306.5	1.41	2100	6	2	1.02	0.007	-1.33	-4.5	36.22	920
epeate	ed bend	ing and e	expansior	n is not re	commen	ded.									

#### **Operating Temperature Range:**

°F: -4 to 842 °C: -20 to 450

#### Notes:

• The permissible pressure varies with operating temperature.



### TOTAKU IT-13



#### **Standard Dimensions and Properties**

#### Features

- Made with aluminum polyester cloth and galvanized steel sheet, suitable for use at temperatures up to 266°F (130°C).
- Uses a special laminated film to reduce particle emission caused by surface abrasion.
- Fully flexible and easy to expand and contract, simplifying storage, handling, and transport.

#### Applications

- Ideal for air supply and exhaust in cleanrooms and other environments requiring low particle emission.
- Suitable for intake and exhaust in hot air generation equipment.

#### Notes

 This product uses materials designed to minimize dust generation; however, under certain conditions (such as temperature, fluid type, or pressure), particle emission may still occur. Please verify emission characteristics based on your operating conditions before use.

TOTAKU IT-13, 2 inches ( $\phi$ 50 mm); Conventional Heat-Resistant Duct,

A 12-inch (30 cm) duct sample is placed in a clean bench (Class 100)

within a cleanroom and subjected to expansion and contraction for

1 minute to induce particle emission, which is then measured.

Climate Instruments Laser Particle Counter (JQA-certified),

Model CI-500 with a semiconductor laser light source

Particle Size Range (µm): 0.3, 0.5, 1.0, 2.0, 5.0, 10.0

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	ıter neter	Refer Wei	ence ght	Len	gth	Allowable (at room te	Pressure mperature)	Allowabl Pres (at room t	le Vacuum ssure emperature)	Allowable B (to the center a	end Radius xis of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
2	50	2.01	51.0	2.15	54.5	0.25	365	16	5	1.02	0.007	-2.51	-8.5	4.72	120
2.5	65	2.66	67.5	2.81	71.5	0.30	445	16	5	1.02	0.007	-2.36	-8.0	5.51	140
3	75	2.99	76.0	3.15	80.0	0.35	520	16	5	1.02	0.007	-2.07	-7.0	6.30	160
4	100	4.04	102.5	4.17	106.0	0.42	630	16	5	1.02	0.007	-1.92	-6.5	8.27	210
5	125	5.02	127.5	5.16	131.0	0.51	755	16	5	1.02	0.007	-1.92	-6.5	9.84	250
6	150	5.98	152.0	6.10	155.0	0.62	925	16	5	1.02	0.007	-1.77	-6.0	11.81	300
7	175	6.95	176.5	7.09	180.0	0.71	1050	16	5	1.02	0.007	-1.48	-5.0	11.81	300
8	200	7.95	202.0	8.07	205.0	0.82	1225	16	5	1.02	0.007	-1.33	-4.5	15.75	400
10	250	9.96	253.0	10.08	256.0	1.04	1550	16	5	1.02	0.007	-0.89	-3.0	23.62	600
12	300	11.93	303.0	12.05	306.0	1.24	1840	16	5	1.02	0.007	-0.89	-3.0	23.62	600

**Test Samples** 

2 inches (φ50 mm)

**Cleaning Method** Clean air wash

**Measurement Method** 

**Measurement Equipment** 

Sample Flow Rate: 1 CF/Min

#### **Particle Emission Comparison**



Note: The data shown represents measured values and are not guaranteed specifications.

Notes:

#### **Operating Temperature Range:**

The permissible pressure varies with operating temperature.

°F: -4 to 266 °C: -20 to 130 16 of 16 | TOTAKU Ducting Hoses



## TOTAKU General Suction/Discharge Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

LINE ACE	02
SHIMETAC for TOTAKU LINE ACE	03
SD-A	04
SD-A2	05
SD-C	06
SD-C3	07

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

## TOTAKU LINE ACE



#### Features

- This is a pressure-resistant type of SD hoses.
- It is equipped with a reinforcement cord, providing an allowable pressure of 72.5 psi (0.50 MPa). For diameters of 10 inches (φ250) and 12 inches (φ300), the allowable pressure is 36.3 psi (0.25 MPa).

#### Applications

- Suitable for general discharge and suction use.
- Ideal for submersible pump startups, steep slopes, and hose / suspension applications.
- Effective for suction use in tank trucks.







Aluminum Crimping (up to 4in. Diameter, φ100) (Victaulic S Collar)

Clamp Mounting Example



TOTAKU Power Band Tightening (JIS Flange) (2in. to 6in. Diameter

(φ50 to φ150))



External Clamp Joint for LINE ACE (3in. and 4in. Diameter (φ75 and φ100))

#### **Standard Dimensions and Properties**

Non Dian	ninal neter	In Diam	ner neter	Ou Dian	iter neter	Pit	tch	Refe We	rence ight	Len	gth	Allowable (at room ter	Pressure nperature)	Allowable Be (to the cer) of the l	end Radius ater axis hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.37	34.9	0.30	7.5	0.27	400	164	50	72.52	0.50	4.13	105
1.25	32	1.26	32.0	1.67	42.5	0.33	8.5	0.35	520	164	50	72.52	0.50	4.72	120
1.5	38	1.50	38.0	1.94	49.2	0.35	9.0	0.46	680	164	50	72.52	0.50	5.91	150
2	50	2.00	50.8	2.50	63.4	0.39	10.0	0.64	950	164	50	72.52	0.50	8.86	225
2.5	65	2.50	63.5	3.09	78.5	0.56	14.3	0.88	1305	65/164	20/50	72.52	0.50	10.63	270
3*	75	3.00	76.2	3.62	92.0	0.59	15.1	1.10	1635	65/164	20/50	72.52	0.50	14.76	375
4*	100	4.00	101.6	4.72	120.0	0.65	16.4	1.76	2620	65/164	20/50	72.52	0.50	21.26	540
5	125	4.96	125.9	6.00	152.5	0.87	22.0	2.84	4220	65	20	72.52	0.50	24.80	630
6	150	5.96	151.4	7.09	180.0	0.94	24.0	3.94	5860	65	20	72.52	0.50	30.71	780
8	200	8.02	203.7	9.33	237.0	1.10	28.0	5.77	8590	32	10	72.52	0.50	47.24	1200
10	250	10.00	254.0	11.61	295.0	1.26	32.0	9.10	13540	16	5	36.26	0.25	74.41	1890
12	300	12.00	304.8	13.66	347.0	1.34	34.0	10.93	16260	16	5	36.26	0.25	86.22	2190

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. For tightening with Totaku Power Bands, we recommend sizes 2 inches (φ50) to 6 inches (φ150). In this case, the allowable pressure is 43.5 psi (0.30 MPa). For sizes 8 inches (φ200) and above, we recommend crimping for safety.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.



### SHIMETAC for TOTAKU LINE ACE

[Applicable Sizes: 1 inch ( $\varphi$ 25)\*, 1.5 inches to 4 inches ( $\varphi$ 38 to  $\varphi$ 100)] \*For 1 inch ( $\varphi$ 25), use the "SHIMETAC for TOTAKU ECO LINE"

#### SHIMETAC for TOTAKU LINE ACE



Part Number 92311-025 (1 in. Diameter (φ25), Stainless Steel Bolt) Part Number 92298- (1.5 in. to 4 in. Diameter (φ38-φ100), Steel Structure Bolt) Part Number 92302- (1.5 in. to 4 in. Diameter (φ38-φ100), Stainless Steel Bolt) Material: FRPP (Fiber-Reinforced Polypropylene)

#### Features

- Lightweight due to resin construction
- Rust-free because of resin material
- High durability

#### Repeated pressure resistance tests were conducted:

SHIMETAC were attached to both ends of a straight LINE ACE hose, and repeated pressures ranging from 0 to 72.5 psi (0.5 MPa) were applied at 20-second intervals.

**Result:** All sizes showed no abnormalities after 100,000 cycles.

#### Notes

- Be sure to use the *dedicated fittings* for SHIMETAC.
- The fittings shown below are examples.

#### **Dedicated Fittings for SHIMETAC**



**PT (Pipe Taper) SHIMETAC shank (Resin)\*** \* Available sizes: 1.5 inches (φ38) and 2 inches (φ50) only.



Flanged SHIMETAC shank (Steel Structure)



Flanged SHIMETAC shank with Tapered Socket (*PVC*)

**Hose Installation** 

Example



M1 SHIMETAC shank (Steel Structure)



Double-Ended SHIMETAC shank (Steel Structure)









### TOTAKU SD-A

Part Number - 22101





**Standard Dimensions and Properties** 

# Clamp Mounting Example

Corrugation Sealing and Flat Band Clamp (JIS Flange)

#### Features

- The corrugated outer surface (with a smooth inner surface) ensures outstanding flexibility.
- The completely transparent material makes it easy to monitor the internal fluids.

#### Applications

- Suitable for both suction and discharge, but especially ideal for suction use.
- Useful for irrigation.
- Effective for suction and drainage at industrial and civil engineering sites

#### **Compatibility Chart for Steel and PVC Pipes**

Hose N Diam	ominal leter			Ap	plicable	Pipe Ty	ре		
			ASTM:A5	3 Type I	-	JP (A	standar <i>STM:D178</i>	d PVC pi Sequivale	pe nt)
inch	mm	Nom Diam	inal eter	Ou Dian	iter neter	Norr Diarr	ninal Neter	Ou Diam	ter leter
		inch	mm	inch	mm	inch	mm	inch	mm
	60	1.97	50	2.38	60.5	2.0	50	2.36	60
3	75	2.56	65	3.00	76.3	2.6	65	2.99	76
3.5	90	3.15	80	3.51	89.1	3.0	75	3.50	89
4	100	3.54	90	4.00	101.6	-	-	-	-
4.5	115	3.94	100	4.50	114.3	3.9	100	4.49	114
6.5	165	5.91	150	6.50	165.2	5.9	150	6.50	165

For installation, insert directly and secure with an SY band.

#### Allowable Bend Radius Nominal Inner Reference Allowable Pressure **Outer Diameter** Pitch Length (to the center axis Weight Diameter Diameter (at room temperature) of the hose) inch mm inch mm inch mm inch mm lbs/ft q/m feet MPa inch m psi mm 0.5 0.51 0.71 18.0 0.22 0.07 105 98 30 43.51 0.30 1.77 45 13 13.0 5.5 0.75 164 54 19 0.75 19.0 0.97 24.7 0.26 6.5 0.11 160 50 43.51 0.30 2.13 1 25 1.00 25.4 1.25 31.8 0.30 7.5 0.17 250 164 50 43.51 0.30 2.72 69 0.33 1.25 32 1 26 32.0 1.54 39.0 8.5 0.22 330 164 50 36.26 0.25 3.31 84 1.5 38 1.50 38.0 1.80 45.8 0.35 9.0 0.31 465 164 50 36.26 0.25 5.08 129 2 50 2.00 50.8 2.34 59.5 0.39 10.0 0.47 695 164 50 36.26 0.25 6.50 165 60 2.38 60.5 2.73 69.3 039 10.0 0.54 800 164 50 36.26 0.25 6.50 165 2.5 65 2.50 63.5 2.94 74.6 0.56 14.3 0.67 995 65/164 20/50 36.26 0.25 7.68 195 3\* 75 3.00 76.2 3.51 89.1 0.59 15.1 0.94 1405 65/164 20/50 36.26 0.25 8.27 210 3.5\* 89.1 1.48 2200 65/164 20/50 21.76 0.15 11.81 90 3.51 4.17 106.0 0.64 16.2 300 4\* 100 4.00 101.6 4.63 117.6 0.65 1.66 2470 65/164 20/50 21.76 0.15 12.99 330 16.4 4.5\* 115 4.50 114.3 5.19 131.8 0.72 18.4 1.84 2740 65 20 21.76 0.15 15.35 390 65 5 125 4.96 125.9 5.65 143.6 0.87 22.0 2.24 3330 20 21.76 0.15 15.94 405 65 6 150 6.00 152.4 6.77 172.0 0.87 22.0 3.04 4530 20 21.76 0.15 26.57 675 6.5\* 6.50 165.2 726 184.5 0.91 23.0 3.19 4740 65 20 21.76 0 1 5 38.39 975 165 8 200 8.02 203.7 9.19 233.5 0.91 23.0 6.15 9150 32 10 21.76 0.15 41.34 1050

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

### TOTAKU SD-A2



#### Features

- This is a lightweight version of TOTAKU SD-A.
- It provides enhanced flexibility compared to TOTAKU SD-A.

#### Applications

- Suitable for both suction and discharge, but especially ideal for suction use.
- Useful for irrigation.
- Effective for suction and drainage at industrial and civil engineering sites



#### **Standard Dimensions and Properties**

Norr Diarr	ninal neter	In Dian	ner neter	Ou Diar	uter neter	Pi	tch	Refer Wei	ence ght	Len	gth	Allowable (at room ter	Pressure mperature)	Allowable I (to the center of	Bend Radius axis of the hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.21	30.8	0.30	7.5	0.13	200	164	50	29.01	0.20	2.76	70
1.25	32	1.26	32.0	1.50	38.2	0.33	8.5	0.17	255	164	50	21.76	0.15	3.15	80
1.5	38	1.50	38.0	1.76	44.6	0.35	9.0	0.26	385	164	50	21.76	0.15	3.54	90
2	50	2.00	50.8	2.28	58.0	0.39	10.0	0.36	540	164	50	14.50	0.10	5.91	150
2.5	65	2.50	63.5	2.87	73.0	0.56	14.3	0.54	810	164	20/50	14.50	0.10	7.09	180
3*	75	3.00	76.2	3.44	87.5	0.59	15.1	0.76	1135	65/164	20/50	14.50	0.10	8.27	210
4*	100	4.00	101.6	4.53	115.0	0.65	16.4	1.32	1965	65/164	20/50	14.50	0.10	11.81	300
5	125	4.96	125.9	5.57	141.6	0.87	22.0	1.69	2520	65	20	14.50	0.10	13.78	350

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

### TOTAKU SD-C





#### Features

- Smooth surfaces on both the interior and exterior.
- Offers better pressure resistance than TOTAKU SD-A.
- The transparent soft section enables easy monitoring of transported materials.

#### Applications

- Suitable for both suction and discharge, but especially ideal for discharge use.
- Useful for suction and drainage in agriculture, industry, and civil construction.



#### **Standard Dimensions and Properties**

Nom Diam	ninal neter	Inner D	iameter	Outer [	Diameter	Referenc	e Weight	Len	gth	Allowable (at room te	Pressure	Allowable I (to the c of the	Bend Radius enter axis e hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
0.75	19	0.75	19.0	0.95	24.2	0.15	220	164	50	87.02	0.60	4.53	115
1	25	1.00	25.4	1.23	31.2	0.23	340	164	50	72.52	0.50	9.45	240
1.25	32	1.26	32.0	1.54	39.2	0.34	510	164	50	65.27	0.45	13.39	340
1.5	38	1.50	38.0	1.81	46.0	0.44	650	164	50	58.02	0.40	13.78	350
2	50	2.00	50.8	2.40	61.0	0.75	1120	164	50	58.02	0.40	19.69	500
2.5	65	2.50	63.5	2.94	74.8	1.02	1525	65/164	20/50	58.02	0.40	23.62	600
3*	75	3.00	76.2	3.46	88.0	1.27	1885	65/164	20/50	58.02	0.40	30.51	775
3.5*	90	3.50	88.9	3.96	100.5	1.47	2190	65	20	43.51	0.30	41.93	1065
4*	100	4.00	101.6	4.56	115.8	2.07	3080	65	20	43.51	0.30	45.28	1150
5**	125	5.00	127.0	5.55	141.0	2.46	3660	65	20	36.26	0.25	62.99	1600
6**	150	6.00	152.4	6.61	167.8	3.36	5000	65	20	29.01	0.20	73.82	1875
8**	200	8.00	203.2	8.83	224.4	5.84	8690	32	10	29.01	0.20	118.11	3000

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes. \*\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:** °F: 14 to 122 °C: -10 to 50

- Notes:
  - The permissible pressure varies with operating temperature.
  - Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

### TOTAKU SD-C3



### Standard Dimensions and Properties

#### Allowable Bend Radius Nominal Allowable Pressure **Inner Diameter Outer Diameter Reference Weight** Length (to the center axis Diameter (at room temperature) of the hose) inch mm inch mm inch mm lbs/ft g/m feet m psi MPa inch mm 1 25 1.00 25.4 1.20 30.6 0.19 280 164 50 87.02 0.60 10.83 275 1.25 32 1.26 32.0 1.48 37.6 0.26 390 164 50 72.52 0.50 14.76 375 38 1.50 0.33 485 58.02 18.70 475 1.5 38.0 1.73 44.0 164 50 0.40 2 50 2.00 50.8 2.30 58.5 0.55 825 164 50 50.76 0.35 24.02 610 2.5 65 2.50 63.5 2.86 72.6 0.80 1195 65/164 20/50 50.76 0.35 31.50 800 3\* 3.00 76.2 3.37 85.5 0.99 1470 65/164 20/50 50.76 0.35 53.54 75 1360 4\* 100 4.00 101.6 2530 65/164 20/50 0.30 57.09 4.45 113.0 1.70 43.51 1450 5 125 5.00 127.0 5.47 139.0 2.22 3300 65 20 43.51 0.30 98.43 2500 6.00 2.93 36.26 2900 6 150 152.4 6.54 166.0 4360 65 20 0.25 114.17 200 8.00 221.2 5.11 7610 10 29.01 3000 8 203.2 8.71 32 0.20 118.11

Features

Applications

discharge use.

construction.

This is a lightweight version of TOTAKU SD-C.

Suitable for both suction and discharge, but especially ideal for

Useful for suction and drainage in agriculture, industry, and civil

•

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.



## TOTAKU Anti-Static Hoses and Ducts

### For powders and granules

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

SD-CE	02
SD-AS	03
DUCT-AS	04

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

• Equipped with a built-in copper grounding wire for enhanced static

• Suitable for transporting powders and granules (non-food items).

• Transparent design allows for easy visual confirmation of

### TOTAKU SD-CE



#### **Standard Dimensions and Properties**

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Refei Wei	rence ght	Leng	gth	Allowable (at room ten	Pressure perature)	Allowable Bo (to the center a)	end Radius (is of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.33	33.7	0.38	565	164	50	72.52	0.50	9.45	240
1.25	32	1.26	32.0	1.65	41.8	0.49	735	164	50	65.27	0.45	13.39	340
1.5	38	1.50	38.0	1.89	48.0	0.58	870	164	50	58.02	0.40	13.78	350
2	50	2.00	50.8	2.50	63.5	0.98	1455	164	50	58.02	0.40	19.69	500
2.5	65	2.50	63.5	3.02	76.8	1.28	1905	65/164	20/50	58.02	0.40	23.62	600
3*	75	3.00	76.2	3.54	89.8	1.52	2260	65/164	20/50	58.02	0.40	30.51	775
3.5*	90	3.50	88.9	4.05	102.8	1.82	2710	65	20	43.51	0.30	41.93	1065
4*	100	4.00	101.6	4.65	118.0	2.43	3620	65	20	43.51	0.30	45.28	1150
5	125	5.00	127.0	5.63	143.0	2.91	4330	65	20	36.26	0.25	62.99	1600
6	150	6.00	152.4	6.73	171.0	3.95	5880	65	20	29.01	0.20	73.82	1875
8	200	8.00	203.2	8.92	226.5	6.69	9960	32	10	29.01	0.20	118.11	3000

Features

Applications

electricity prevention.

transported materials.

• Ideal for transporting resin pellets.

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### Operating Temperature Range:

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

Scan, tap, or touch for product videos





Method for Extracting Grounding Wire

### TOTAKU SD-AS



#### **Standard Dimensions and Properties**

#### Features

- Made with a specially formulated soft resin that provides longlasting static electricity prevention (refer to the "Anti-Static Effect" table below for details).
- The clear green material allows for visual confirmation of transported items

#### Applications

- Ideal for transporting resin pellets.
- Suitable for transporting powders and granules (non-food items).

#### **Anti-Static Effect**

Product Name	General-Purpose	TOTAKU SD-AS
Conveying Line	Product φ38	(Anti-Static φ38)
Soft PVC Conveying Line	1600Volt	100Volt
Rigid PVC Conveying Line	33000Volt	100Volt

Nominal Inner Diameter Diameter		Outer Diameter		Pi	tch	Refei Wei	rence ight	Len	gth	Allowable (at room ter	Pressure nperature)	Allowable Bend Radius (to the center axis of the hose)			
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1	25	1.00	25.4	1.21	30.8	0.30	7.5	0.13	200	164	50	29.01	0.20	2.76	70
1.25	32	1.26	32.0	1.50	38.2	0.33	8.5	0.17	255	164	50	21.76	0.15	3.15	80
1.5	38	1.50	38.0	1.76	44.6	0.35	9.0	0.26	385	164	50	21.76	0.15	3.54	90
2	50	2.00	50.8	2.28	58.0	0.39	10.0	0.36	540	164	50	14.50	0.10	5.91	150
2.5	65	2.50	63.5	2.87	73.0	0.56	14.3	0.54	810	65/164	20/50	14.50	0.10	7.09	180
3*	75	3.00	76.2	3.44	87.5	0.59	15.1	0.76	1125	65/164	20/50	14.50	0.10	8.27	210
4*	100	4.00	101.6	4.53	115.0	0.65	16.4	1.32	1965	65/164	20/50	14.50	0.10	11.81	300
5	125	4.96	125.9	5.57	141.6	0.87	22.0	1.69	2520	65	20	14.50	0.10	13.78	350
6	150	6.00	152.4	6.77	172.0	0.87	22.0	3.04	4530	65	20	21.76	0.15	26.57	675

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### **Material Properties**

Volume Resistivity $\Omega \cdot cm$ $2.7 \times 108$ $4.2 \times 10^{11}$ JIS	K-6911
Surface Resistivity         Ω         9.8×108         3.5×10 <sup>12</sup> JIS	K-6911
Charge Decay Time 50% sec 0.01 0.64 Tem	perature:
Charge Decay Time 90%         sec         0.01         11.10         73	F (23°C)
Charge Decay Time 100% sec 0.02 30.30 Hum	idity: 60%

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.



### TOTAKU DUCT-AS



#### **Standard Dimensions and Properties**

#### Features

- This is the duct type of the TOTAKU SD-AS hose.
- Made with a specially formulated soft resin that provides longlasting static electricity prevention (refer to the "Anti-Static Effect" table below for details).

#### Applications

- Suitable for exhaust in environments where static electricity must be avoided.
- Ideal for dust collection in woodworking machinery.
- Also suitable for transporting non-food powders.

#### Anti-Static Effect

Product Name	General-Purpose	TOTAKU SD-AS
Conveying Line	Product φ38	(Anti-Static φ38)
Soft PVC Conveying Line	1600Volt	100Volt
Rigid PVC Conveying Line	33000Volt	100Volt

																All	
Nominal Inner Diameter Diameter		Outer Diameter		Pitch		Reference Weight		Length		(at room temperature)		Depressurization (at room temperatur		(to the center axis of the hose)			
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inHg	kPa	inch	mm
1.25	32	1.28	32.4	1.52	38.6	0.33	8.4	0.15	220	164	50	8.70	0.06	-19.49	-66.0	1.26	32
1.5	38	1.47	37.3	1.75	44.5	0.36	9.2	0.20	295	164	50	8.70	0.06	-19.49	-66.0	1.50	38
2	50	1.99	50.6	2.37	60.2	0.39	10.0	0.38	560	98	30	7.25	0.05	-19.49	-66.0	1.97	50
2.5	65	2.46	62.4	2.83	72.0	0.47	12.0	0.41	615	98	30	5.80	0.04	-19.49	-66.0	2.56	65
3*	75	3.01	76.4	3.40	86.4	0.51	13.0	0.52	775	98	30	5.80	0.04	-9.74	-33.0	2.95	75
3.5*	90	3.50	88.9	3.94	100.1	0.53	13.5	0.64	945	98	30	4.35	0.03	-9.74	-33.0	3.54	90
4*	100	4.00	101.6	4.42	112.2	0.59	15.0	0.77	1145	98	30	4.35	0.03	-6.35	-21.5	3.94	100
5	125	4.96	125.9	5.42	137.7	0.83	21.0	0.91	1350	65	20	2.90	0.02	-5.91	-20.0	4.92	125
6	150	6.00	152.4	6.49	164.8	0.79	20.0	1.09	1620	65	20	2.90	0.02	-4.28	-14.5	5.91	150

Sizes marked with an asterisk (\*) can be directly connected to steel pipes. For details, please refer to the Compatibility Chart for Steel and PVC Pipes.

#### **Operating Temperature Range:**

Notes:

°F: -14 to 122 °C: -10 to 50

• The permissible pressure varies with operating temperature.







## TOTAKU Pressure and Abrasion Resistant Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

LINE POWER-AT	02
SHIMETAC for LINE POWER-AT	03
LINE POWER-ATS	04
LINE POWER-ATL	05
LINE POWER-WA	06
LINE POWER-C	07

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

### **TOTAKU LINE POWER-AT**

Part Number - 26124







#### Features

- Exceptional pressure resistance with an allowable pressure of 145 psi (1.00 MPa) at normal temperature, built to minimize stretch under pressure.
- The inner layer is made from abrasion-resistant rubber, offering outstanding durability.
- Engineered to withstand external pressure with minimal deformation.

#### Applications

- Suction and discharge of muddy water in civil engineering projects.
- Suction and discharge of materials like sand, gravel, and sludge.
- Ideal for dredging and land reclamation work.
- Suction and discharge of powdered and granular materials, such as cement.
- Transport of high-viscosity substances, and transfer over long vertical distances.

#### Cautions

• Avoid long-term storage outdoors, as this may cause cracks to form due to ozone degradation.

Non Dian	ninal neter	In Dian	ner neter	Ou Dian	iter neter	Pit	tch	Refe We	rence ight	Leng	Length Allowable (at room te		Pressure nperature)	Allowable Be (to the cer of the l	end Radius nter axis hose)
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
2	50	2.00	50.8	2.74	69.5	0.39	10.0	1.16	1725	65/164	20/50	145.04	1.00	23.62	600
2.5	65	2.50	63.5	3.39	86.0	0.56	14.3	1.53	2270	65/164	20/50	145.04	1.00	29.53	750
3	75	3.00	76.2	3.92	99.5	0.59	15.1	1.87	2790	65/164	20/50	145.04	1.00	29.53	750
4	100	4.00	101.6	5.08	129.0	0.67	17.0	2.96	4400	65/164	20/50	145.04	1.00	49.21	1250
5	125	5.00	127.0	6.28	159.5	0.87	22.0	4.11	6110	65	20	145.04	1.00	66.93	1700
6	150	6.00	152.4	7.38	187.5	0.87	22.0	5.20	7740	65	20	145.04	1.00	78.74	2000
8	200	8.00	203.2	9.74	247.5	0.98	25.0	8.90	13250	32	10	145.04	1.00	88.58	2250

For the maximum length, additional shipping charges may apply depending on the batch. Please confirm this when placing your order.

#### The TOTAKU Power Band can be installed on-site.

(For 8 in ( $\varphi$ 200), crimping is recommended for added safety.)

- Pre-install the TOTAKU Power Band onto the hose, and then insert the fitting.
- Use a torque wrench to tighten the bolts. Be cautious not to overtighten, as it could damage the hose.

Note: For on-site installation, take safety precautions to prevent accidents caused by fittings becoming loose. It is recommended to secure the TOTAKU Power Band to the flange or connection points using wire or binding materials

#### Operating Temperature Range: Notes:

°F: 14 to 122 °C: -10 to 50

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

#### **Tightening Torque:**

2 in (φ50), 2.5 in (φ65): 10.84 lb-ft (14.7 N·m)
3 in (φ75): 14.46 lb-ft (19.6 N·m)
4 in (φ100), 5 in (φ125): 18.07 lb-ft (24.5 N·m)
6 in (φ150), 8 in (φ200): 21.69 lb-ft (29.4 N·m)

Scan, tap, or touch for product videos



#### **Standard Dimensions and Properties**

### SHIMETAC for LINE POWER-AT

Applicable Sizes: 2 in (φ50 mm) to 6in (φ150mm)

#### SHIMETAC for LINE POWER-AT



#### Features

- The allowable pressure with a SHIMETAC connection matches the allowable pressure of the hose itself.
- Fittings can be easily attached and removed on-site.

#### Notes

- Be sure to use the *dedicated fittings* for SHIMETAC.
- The fittings shown below are examples.

#### **Dedicated Fittings for SHIMETAC**







Hose Installation Example



S Collar with SHIMETAC Shank (Steel Structure)

#### TOTAKU LINE POWER-AT Standard Fittings and Band Allowable Pressure Table (Normal Temperature)

Diameter		SHIMETAC Tightning		Aluminum Crimping with Locking Mechanism		Structural Steel Crimping with Locking Mechanism		Diameter		TOTAKU Band Tig	l Power htening	Aluminum Crimping without Locking Mechanism		
inch	mm	psi	Мра	psi	Мра	psi	Мра	inch	mm	psi	Мра	psi	Мра	
2	50	145.04	1.00	145.04	1.00	_	-	2	50	72.52	0.50	101.53	0.70	
2.5	65	145.04	1.00	145.04	1.00	_	-	2.5	65	72.52	0.50	101.53	0.70	
3	75	145.04	1.00	145.04	1.00		-	3	75	72.52	0.50	101.53	0.70	
4	100	145.04	1.00	145.04	1.00		-	4	100	72.52	0.50	101.53	0.70	
5	125	145.04	1.00	_	-	145.04	1.00	5	125	72.	52	0	.50	
6	150	145.04	1.00	_	-	145.04 1.00		6	150	72.	52	0.50		
8	200		-	_	_	145.04 1.00		8	200	72.	52	0	.50	



### **TOTAKU LINE POWER-ATS**







Crimping with Locking Mechanism (Victaulic S Collar)

#### Features

- A large-diameter version of the TOTAKU LINE POWER-AT.
- Designed with a thicker layer of abrasion-resistant rubber compared to the standard TOTAKU LINE POWER-AT.

#### Applications

- Suction and discharge of sand, gravel, sludge, and grains during harvest.
- Suitable for dredging and land reclamation projects.
- Suction and discharge of powdered and granular materials, such as cement.

#### Cautions

• Avoid long-term storage outdoors, as this may lead to cracks caused by ozone degradation.

#### **Installation of Fittings**

• Fitting installation is performed at our factory.

#### **Standard Dimensions and Properties**

Nom Diam	inal eter	l Inner er Diameter		Outer Diameter		Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
10*	250	10.08	256.0	12.01	305.0	1.00	25.5	12.93	19240	16	5	145.04	1.00	187.01	4750
12*	300	12.13	308.0	14.13	359.0	1.10	28.0	15.31	22780	16	5	72.52	0.50	196.85	5000

For the maximum length, additional shipping charges may apply depending on the batch. Please confirm this when placing your order.

\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

### **TOTAKU LINE POWER-ATL**





#### Features

• A lightweight version of the TOTAKU LINE POWER-AT.

#### Applications

- Suction and discharge of muddy water for civil engineering projects, such as mud-water shield construction.
- Suction and discharge of powdered and granular materials, such as cement.
- Transport of high-viscosity substances and transfer over long vertical distances.

#### Cautions

• Avoid long-term storage outdoors, as this may lead to cracks caused by ozone degradation.



#### **Standard Dimensions and Properties**

Nor Diar	ninal neter	In Diar	inner Outer ameter Diameter		iter neter	Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
4*	100	4.00	101.6	4.96	126.0	0.65	16.4	2.42	3600	65	20	101.53	0.70	39.37	1000
6*	150	6.00	152.4	7.22	183.5	0.87	22.0	4.31	6420	65	20	101.53	0.70	68.90	1750

For the maximum length, additional shipping charges may apply depending on the batch. Please confirm this when placing your order.

\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:**

°F: 14 to 122 °C: -10 to 50

Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

### **TOTAKU LINE POWER-WA**

Part Number - 26109





#### Features

• With an allowable pressure of 218 psi (1.50 MPa) at normal temperature, this hose offers the highest pressure resistance among pressure- and abrasion-resistant hoses.

#### Applications

- Suitable for general water supply, cooling water, and wastewater.
- Ideal for water supply and discharge in general factories, civil engineering and construction sites, and shipbuilding facilities.

#### **Durability Performance (Repeated Water Pressure Test)**

Hoses in a straight configuration were repeatedly pressurized from 0 to 218 psi (0 to 1.50 MPa) at 20-second intervals.

Result: No abnormalities were found after 50,000 cycles for all sizes.

#### **Installation of Fitting**

• Fitting installation is performed at our factory.

#### **Standard Dimensions and Properties**

Norr Diarr	ninal neter	Inner D	Diameter	Ou Dian	iter neter	Refe We	rence ight	Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1.5	38	1.52	38.5	2.07	52.5	0.93	1380	65/164	20/50	217.56	1.50	19.69	500
2	50	2.00	50.8	2.61	66.2	1.34	1990	65/164	20/50	217.56	1.50	19.69	500
2.5	65	2.50	63.5	3.11	78.9	1.74	2595	65/164	20/50	217.56	1.50	24.61	625
3	75	3.01	76.5	3.70	93.9	2.40	3575	65/164	20/50	217.56	1.50	31.50	800
4	100	4.00	101.6	4.76	121.0	3.59	5340	65	20	217.56	1.50	56.10	1425

#### **Operating Temperature Range:**

#### Notes:

• The permissible pressure varies with operating temperature.

°F: -4 to 194 °C: -20 to 90

#### Discharge:

Suction:

°F: -4 to 176 °C: -20 to 80

- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa)
- is feasible at room temperature.

### **TOTAKU LINE POWER-C**

Part Number - 26101





#### Features

- A fully resin-based pressure-resistant hose.
- Excellent pressure resistance with minimal elongation.
- The outer surface is protected by rigid PVC, making it highly resistant to external abrasion and preventing exposure of the reinforcement fibers.

#### Applications

- For water use (e.g., high head water transfer or the discharge / section of a submersible pump).
- Transport of high-viscosity substances on steep slopes.
- Suitable for both suction and delivery applications.

#### **Installation of Fitting**

• Fitting installation is performed at our factory.

Nom Diam	ninal neter	In Diar	ner neter	Ou Diar	ıter neter	Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1.25	32	1.26	32.0	1.77	45.0	0.69	1020	65/164	20/50	145.04	1.00	16.73	425
1.5	38	1.50	38.2	2.01	51.0	0.82	1225	65/164	20/50	145.04	1.00	19.69	500
2	50	2.00	50.8	2.56	65.0	1.09	1625	65/164	20/50	145.04	1.00	31.50	800
2.5	65	2.50	63.5	3.16	80.3	1.66	2470	65/164	20/50	145.04	1.00	37.40	950
3*	75	3.00	76.2	3.72	94.5	2.06	3060	65/164	20/50	145.04	1.00	49.21	1250
4*	100	4.00	101.6	4.92	125.0	3.70	5510	65	20	101.53	0.70	76.77	1950

\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### Operating Temperature Range:

°F: 14 to 122 °C: -10 to 50

e: Notes:

• The permissible pressure varies with operating temperature.

 Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.



### TOTAKU Mortar Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

LINE POWER-ABRW 02 LINE POWER-CV 03

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

### **TOTAKU LINE POWER-ABRW**







Inner Tube Expansion and Outer Tube Crimping\* (Victaulic S Collar) \*This process eliminates uneven surfaces inside the hose fitting, ensuring smooth internal flow.

#### **Standard Dimensions and Properties**

#### Features

• The inner surface is made of rubber, providing superior pressure resistance and durability compared to TOTAKU LINE POWER-CV.

#### Applications

- Intermediate and terminal hose for mortar pumping.
- Suitable for transporting highly viscous materials and use on steep inclines.

#### Cautions

• This hose is designed exclusively for discharge.

#### **Installation of Fitting**

• Fitting installation is performed at our factory.

Norr Diarr	ninal neter	Inı Dian	ner neter	Ou Diam	ter neter	Refer Wei	ence ght	Len	gth	Allowable (at room ter	Pressure mperature)	Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	ft	m	psi	MPa	inch	mm
1.5	40	1.54	39.0	2.19	55.7	0.91	1355	65	20	217.56	1.50	25.59	650
2	50	1.99	50.5	2.60	66.0	1.04	1555	65	20	217.56	1.50	35.43	900

#### Operating Temperature Range:

°C: —

Suction

#### Notes:

• The permissible pressure varies with operating temperature.

**Discharge** °F: 32 to 122 °C: 0 to 50

°F: —

• A durable resin hose with pressure and abrasion resistance.

Designed specifically as an end hose for mortar pumping.

• This hose is designed exclusively for discharge.

• Fitting installation is performed at our factory.

Built to withstand external pressure without flattening or buckling.

### **TOTAKU LINE POWER-CV**







Aluminum Crimping (Victaulic G Collar)

#### **Standard Dimensions and Properties**

#### Nominal Inner Outer Reference Allowable Pressure Allowable Bend Radius Length Diameter Diameter Diameter Weight (at room temperature) (to the center axis of the hose) inch inch inch lbs/ft MPa inch mm mm mm g/m ft m psi mm 20/50 145.04 1.5 40 1.57 40.0 2.05 52.0 0.76 1135 65/164 1.00 23.62 600 2 50 2.00 50.8 2.52 64.0 1.02 1525 65/164 20/50 145.04 1.00 29.53 750

Features

Applications

Installation of Fitting

Cautions

•

#### **Operating Temperature Range:**

Suction °C:

#### Notes:

• The permissible pressure varies with operating temperature.

#### Discharge °C: 0 to 50 °F: 32 to 122

°F: —

03 of 03 | TOTAKU Mortar Hoses



## TOTAKU Oil-Resistant Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

SD-COR	03
LINE POWER-CVOR	04
LINE POWER-ATO	05
LINE POWER-OT	06

#### Notice:

- The data in this catalog uses values in a straight hose configuration. (The allowable vacuum pressure for duct hoses is measured when the hose is in a straight configuration with both ends fixed.)
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

#### **Important Safety Precautions for Oil-Resistant Hoses**

#### Warning: Improper handling may result in serious injury or accidents.

- Before use, always check the operating conditions (fluid type, flow rate, pressure, and temperature) and ensure the hose is used within the appropriate limits.
- Hoses are consumable and deteriorate over time. If any abnormalities are found during daily or regular inspections, stop using the hose immediately and replace it with a new one.
- Do not install or operate the system in a way that subjects the hose to excessive flow rates (6.6 ft/s [2 m/s]) or sudden flow changes, as this may generate shock pressure exceeding the allowable limit, potentially causing hose failure.
- Do not install the hose in a way that applies excessive tension or load, as this can lead to damage.
- When using the hose for marine refueling, ensure vessel movement does not put tension on the hose.
- Avoid bending the hose too sharply near fittings, as this may lead to early failure.
- For more details, refer to "Hose Handling Precautions" in this catalog.

### We do not provide any warranty for damages resulting from the improper use of hoses, fittings, or hose assemblies.

#### **Oil-Resistant TOTAKU Hoses: Compatible Transport Materials**

Transport Material	TOTAKU SD-COR	TOTAKU LINE POWER-CVOR	TOTAKU LINE POWER-ATO	TOTAKU LINE POWER-OT
Crude Oil	-	-	-	$\checkmark$
Gasoline	-	-	-	$\checkmark$
Kerosene	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$
Diesel fuel	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$
Heavy fuel Oil (HFO)	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$

#### The following TOTAKU hoses are also compatible with oil-resistant applications:

TOTAKU SD-F	TOTAKU SD-HF	TOTAKU DUCT-OR	TOTAKU DUCT-AROR	TOTAKU ECO LINE-HO 100°C	TOTAKU ECO LINE-HO
-	-	-	-	-	-
-	-	-	✓ (VOLATILE FORM ONLY)	-	-
✓	~	✓ (VOLATILE FORM ONLY)	✓ (VOLATILE FORM ONLY)	$\checkmark$	$\checkmark$
$\checkmark$	~	✓ (VOLATILE FORM ONLY)	✓ (VOLATILE FORM ONLY)	-	-
$\checkmark$	$\checkmark$	✓ (VOLATILE FORM ONLY)	✓ (VOLATILE FORM ONLY)	_	-



#### Legend:

✓ = Compatible for full use

✓ (VOLATILE FORM ONLY) = Compatible with the volatile form (vapor or gas) only - = Not compatible with the material

### **TOTAKU SD-COR**

Part Number - 22117





**Standard Dimensions and Properties** 

#### Features

- An all-resin oil-resistant hose.
- Designed with a special oil-resistant resin, making it suitable for transporting oils.

#### Applications

- Used for transporting diesel, kerosene, and Heavy fuel Oil (HFO). (Refer to the Caution.)
- / Suitable for both suction and discharge.

#### Cautions

- For crude oil and gasoline transport, use LINE POWER-OT.
- TOTAKU SD-COR does not have a grounding wire

wable Pressure Allowable Bend Radius
for temperature) (to the center axis of the hose,
MPa inch mm
2 0.50 9.45 240
7 0.45 13.39 340
2 0.40 13.78 350
2 0.40 19.69 500
2 0.40 23.62 600
2 0.40 30.51 775
1 0.30 45.28 1150

#### **Operating Temperature Range:**

#### Notes:

Suction °F: 14 to 140 °C: -10 to 60

Discharge

°C: -10 to 50 °F: 14 to 122

#### • The permissible pressure varies with operating temperature. • Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa)

is feasible at room temperature.

### **TOTAKU LINE POWER-CVOR**

Part Number - 26122





#### **Standard Dimensions and Properties**

#### Features

- Contains reinforcement fibers, offering superior pressure resistance compared to TOTAKU SD-COR.
- Built-in ground wire helps prevent static electricity buildup.

#### Applications

- Ideal for oil transfer in refineries and general industrial facilities.
- Suitable for transporting diesel, kerosene, and Heavy fuel Oil (HFO).

#### Cautions

- Do not store outdoors for extended periods.
- This hose is designed exclusively for discharge.
- For transporting crude oil and gasoline, use LINE POWER-OT.

#### **Installation of Fitting**

• Fitting installation is performed at our factory.

Nom Diam	inal eter	In Dian	ner neter	Ou Diam	ter neter	Refer Wei	rence ght	nce Length ht		Allowable (at room te	Pressure mperature)	Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	ft	m	psi	MPa	inch	mm
1.25*	32	1.26	32.0	1.78	45.2	0.65	960	65/164	20/50	101.53	0.70	19.69	500
1.5	38	1.52	38.5	1.99	50.5	0.76	1125	65/164	20/50	101.53	0.70	23.62	600
2	50	2.00	50.8	2.52	64.0	1.01	1505	65/164	20/50	101.53	0.70	29.53	750

\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:**

Suction

°F: — °C: — Discharge

°F: 14 to 122 °C: -10 to 50

#### Notes:

• The permissible pressure varies with operating temperature.



### **TOTAKU LINE POWER-ATO**

Part Number - 26106





#### Features

- About half the weight of a rubber hose with excellent flexibility.
- Oil-resistant rubber is used for the inner surface.
- Provides anti-static protection with conductive oil-resistant rubber and a built-in ground wire.

#### Applications

- Suitable for transporting Heavy fuel Oil (HFO), kerosene, and diesel.
- Used for loading and unloading from tank trucks, refineries, ships, and tank railcars, as well as oil transfer within general industrial facilities.

Note: At a fluid temperature of 140°F (60°C) [maximum operating temperature range], the allowable pressure is 72.5 psi (0.50 MPa) (ambient temperature: 86°F [30°C]).

#### Cautions

- To prevent cracking from ozone degradation, cap both ends of the hose and store it indoors in a dry area, away from direct sunlight.
- Do not store the hose outdoors, as it may deteriorate.

#### **Installation of Fitting**

• Fitting installation is performed at our factory. *For shipments from our factory, a test report will be included.* 

Non Dian	ninal neter	In Diar	ner neter	Oı Diar	uter neter	Pit	ch	Reference Length Weight		gth	Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)		
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	ft	m	psi	MPa	inch	mm
2	50	2.00	50.8	2.62	66.6	0.39	10.0	1.07	1590	65	20	101.53	0.70	17.72	450
2.5	65	2.50	63.5	3.21	81.5	0.56	14.3	1.32	1970	65	20	101.53	0.70	21.65	550
3	75	3.00	76.2	3.89	98.8	0.59	15.1	1.96	2920	65	20	101.53	0.70	30.51	775
4	100	4.00	101.6	5.12	130.0	0.70	17.7	3.09	4600	65	20	101.53	0.70	49.21	1250
5	125	5.00	127.0	6.18	157.0	0.87	22.0	4.08	6070	65	20	101.53	0.70	59.06	1500
6*	150	6.00	152.4	7.38	187.5	0.87	22.0	5.20	7740	65	20	101.53	0.70	78.74	2000

\* These are made-to-order products. Please contact our company regarding order quantities and other inquiries.

#### Operating Temperature Range:

#### Notes:

°F: -4 to 140 °C: -20 to 60

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.

#### **Standard Dimensions and Properties**

### **TOTAKU LINE POWER-OT**

Part Number - 26108







#### **Standard Dimensions and Properties**

#### Features

- Offers the highest pressure resistance among oil-resistant hoses, with an allowable pressure of 217.5 psi (1.50 MPa).
- Provides anti-static protection with conductive oil-resistant rubber and a steel wire.

#### Applications

- Suitable for transporting crude oil, gasoline, Heavy fuel Oil (HFO), kerosene, and diesel.
- Used for loading and unloading from tank trucks, refineries, ships, and tank railcars, as well as oil transfer within general industrial facilities.

Note: Use only with gasoline that contains 40% or less aromatic content. "Aromatics" refer to aromatic hydrocarbons, including benzene, toluene, and xylene. Most gasoline typically contains 20–30% aromatics.

#### **Durability Performance (Repeated Water Pressure Test)**

- Hoses in a straight configuration were repeatedly pressurized from 0 to 218 psi (0 to 1.50 MPa) at 20-second intervals.
- Result: No abnormalities were found after 50,000 cycles for all sizes.

#### Cautions

- To prevent cracking from ozone degradation, cap both ends of the hose and store it indoors in a dry area, away from direct sunlight.
- Do not store the hose outdoors, as it may deteriorate.

#### **Installation of Fitting**

• Fitting installation is performed at our factory.

Non Dian	ninal neter	In Diar	ner neter	Ou Diar	iter neter	Refer Wei	ence ght	Len	gth	Allowable (at room te	Pressure mperature)	Allowable B (to the center a	end Radius kis of the hose)
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	ft	m	psi	MPa	inch	mm
1.5	38	1.52	38.5	2.02	51.3	0.93	1390	65/164	20/50	217.56	1.50	19.69	500
2	50	2.00	50.8	2.52	64.0	1.23	1835	65/164	20/50	217.56	1.50	19.69	500
2.5	65	2.50	63.5	3.04	77.1	1.70	2530	65/164	20/50	217.56	1.50	24.61	625
3	75	3.01	76.5	3.62	92.0	2.30	3420	65/164	20/50	217.56	1.50	31.50	800
4	100	4.00	101.6	4.69	119.0	3.47	5170	65	20	217.56	1.50	56.10	1425

#### Operating Temperature Range:

Suction

- °F: -4 to 194 °C: -20 to 90
  - -: -4 to 194

**Discharge** °F: -4 to 176 °C: -20 to 80

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.





## TOTAKU Abrasion Resistant Hoses

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

#### **Featured Products**

HERAN	02
HERAN-N	03
HERAN-CL	04
HERAN-ACE	05

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

### **TOTAKU HERAN**

 Part Number - 25101





#### **Standard Dimensions and Properties**

#### Features

- Made with abrasion-resistant rubber, offering approximately three times the abrasion resistance compared to TOTAKU SD-A.
- Equipped with conductive rubber for static electricity prevention.

#### Applications

- Suitable for transporting materials using vacuum conveyors and chutes in factories, ships, shipyards, construction sites, and environmental maintenance.
- Ideal for transporting slurries, sintered cement, gravel, iron ore, and similar items.
- Effective for transporting grains such as rice, barley, and wheat during harvest.

#### Cautions

- Avoid prolonged outdoor use. Store indoors. (There is a risk of cracking due to ozone degradation.)
- Do not use with particulate materials containing oil (powders and fibers). (There is a risk of premature wear due to swelling.)

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1.5	38	1.50	38.0	1.85	47.0	0.35	9.0	0.36	540	164	50	21.76	0.15	5.12	130
2	50	2.00	50.8	2.38	60.5	0.39	10.0	0.55	825	164	50	17.40	0.12	6.50	165
2.5	65	2.50	63.5	2.96	75.1	0.56	14.3	0.74	1105	65/164	20/50	17.40	0.12	7.68	195
3	75	3.00	76.2	3.53	89.6	0.59	15.1	1.06	1570	65/164	20/50	14.50	0.10	8.27	210
3.5	90	3.50	88.9	4.10	104.2	0.64	16.2	1.43	2130	65/164	20/50	14.50	0.10	11.81	300
4	100	4.00	101.6	4.66	118.4	0.65	16.4	1.73	2570	65/164	20/50	14.50	0.10	12.99	330
5	125	4.96	125.9	5.69	144.5	0.87	22.0	2.46	3660	65	20	14.50	0.10	15.94	405
6	150	6.00	152.4	6.77	172.0	0.87	22.0	3.25	4830	65	20	14.50	0.10	26.57	675

#### Operating Temperature Range:

°F: -4 to 122 °C: -20 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature





### TOTAKU HERAN-N







TOTAKU Power Band Tightening

#### Features

- Designed to withstand hot air up to 100°C (approximately 212°F) and handle temperatures up to 120°C (approximately 248°F) in a straight hose configuration.
- Enhanced safety through conductive rubber and the use of steel wire for grounding effects.
- Resistant to ozone degradation compared to TOTAKU HERAN.
- Superior abrasion resistance, along with excellent weather resistance.

#### Applications

- Suitable for transporting materials using vacuum conveyors and chutes in factories, ships, shipyards, construction sites, and environmental maintenance.
- Ideal for transporting slurries, sintered cement, gravel, iron ore, and similar items.
- Effective for transporting grains such as rice, barley, and wheat during harvest

#### Cautions

• Do not use with particulate materials containing oil (powders and fibers). (There is a risk of premature wear due to swelling.)

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
1.5	38	1.50	38.0	1.88	47.8	0.35	9.0	0.38	570	164	50	14.50	0.10	5.31	135
2	50	2.00	50.8	2.46	62.6	0.39	10.0	0.61	905	164	50	14.50	0.10	7.09	180
2.5	65	2.50	63.5	3.03	77.0	0.56	14.3	0.83	1240	65/164	20/50	14.50	0.10	8.86	225
3	75	3.01	76.4	3.62	92.0	0.59	15.1	1.14	1695	65/164	20/50	14.50	0.10	11.81	300
3.5	90	3.50	88.9	4.11	104.5	0.64	16.2	1.41	2100	65/164	20/50	14.50	0.10	15.35	390
4	100	4.00	101.6	4.72	120.0	0.65	16.4	1.76	2620	65/164	20/50	14.50	0.10	22.44	570
5	125	5.00	127.0	5.78	146.8	0.87	22.0	2.59	3860	65	20	14.50	0.10	24.80	630
6	150	6.00	152.4	6.81	173.0	0.87	22.0	3.30	4910	65	20	14.50	0.10	35.43	900
8	200	8.05	204.4	8.90	226.0	0.87	22.0	5.20	7740	32	10	14.50	0.10	41.34	1050

#### **Standard Dimensions and Properties**

#### **Operating Temperature Range:**

#### Suction:

#### °F: -4 to 176 °C: -20 to 80 Discharge:

°F: -4 to 122 °C: -20 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature


# TOTAKU HERAN-CL



### Features

- Abrasion resistance is four times that of TOTAKU HERAN-N. (This value is based on a comparison of abrasion amounts at the initial wear stage, measured 8 hours after testing, with TOTAKU HERAN-N set as the baseline of 1.)
- Transparent design allows visibility of the contents.
- Includes a grounding wire for excellent static electricity prevention.
- The inner surface is extremely smooth, ensuring efficient fluid transport.

#### Applications

- Suitable for transporting slaked lime and activated carbon in waste incineration facilities.
- Ideal for transporting powders and granules prone to static electricity generation.
- Effective for vacuum conveying of sintered cement, gravel, iron ore, and similar materials.

Note: Not suitable for transporting fluids containing oil.

#### **Standard Dimensions and Properties**

Nominal Diameter		Inner Diameter		Outer Diameter		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)		
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm	
1.25*	32	1.26	32.0	1.65	41.8	0.51	765	164	50	58.02	0.40	11.81	300	
1.5	38	1.50	38.0	1.91	48.5	0.61	910	164	50	58.02	0.40	13.78	350	
2	50	2.00	50.8	2.42	61.4	0.83	1230	164	50	58.02	0.40	21.65	550	
2.5	65	2.50	63.5	2.99	76.0	1.21	1805	65/164	20/50	58.02	0.40	31.50	800	
3	75	3.00	76.2	3.52	89.5	1.48	2200	65/164	20/50	58.02	0.40	33.46	850	
3.5	90	3.50	88.9	4.02	102.0	1.69	2510	65/164	20/50	43.51	0.30	43.70	1110	
4	100	4.00	101.6	4.61	117.0	2.24	3340	65/164	20/50	43.51	0.30	49.21	1250	
5	125	5.01	127.3	5.59	142.0	2.73	4060	65	20	36.26	0.25	88.58	2250	
6	150	6.00	152.4	6.67	169.4	3.85	5730	65	20	29.01	0.20	108.27	2750	
8	200	8.00	203.2	8.91	226.4	6.69	9960	32	10	29.01	0.20	157.48	4000	

\* This is a made-to-order product. Please contact our company regarding order quantities and other inquiries.

Sample name	Abrasion mass (g)	Ratio	Abrasion volume (cm <sup>3</sup> )	Ratio
Special Abrasion-Resistant Urethane Resin	0.232	1	0.219	1
ASTM:A53 Type F	13.811	60	1.759	8
ASTM:A312 TP304	10.083	43	1.271	6

## Operating Temperature Range:

°F: -14 to 122 °C: -10 to 50



The permissible pressure varies with operating temperature.

Product

Overview

• Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature.









## TOTAKU HERAN-ACE



## **Standard Dimensions and Properties**

#### Features

- Abrasion resistance is four times that of TOTAKU HERAN-N. (This value is based on a comparison of abrasion amounts at the initial wear stage, measured 8 hours after testing, with TOTAKU HERAN-N set as the baseline of 1.)
- Lightweight and flexible design. ٠
- Pressure rating of approximately 72.5 psi (0.5 MPa) for robust performance.
- Reinforced with durable fibers, this hose is suitable for use in situations where elevation changes may exert tensile loads.
- Includes a grounding wire for excellent static electricity prevention.

### **Applications**

- Suitable for transporting slaked lime and activated carbon in waste • incineration facilities (especially in locations requiring a small bend radius).
- Ideal for suction of soil and sediment using the high-density slurry method.
- Effective for suction and chuting of crushed stone, ore, and similar materials.
- Useful as hoses for dumper trucks Note: Not suitable for transporting fluids containing oil.

Nominal Diameter		Inner Diameter		Outer Diameter		Pitch		Reference Weight		Lengt	:h	Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	feet	m	psi	MPa	inch	mm
4	100	4.00	101.6	4.80	121.8	0.65	16.4	2.18	3240	65	20	72.52	0.50	14.17	360
5*	125	4.96	125.9	5.99	152.2	0.87	22.0	3.04	4530	65	20	72.52	0.50	21.26	540
6*	150	6.00	152.4	7.18	182.4	1.02	26.0	4.11	6110	65	20	72.52	0.50	35.43	900
8*	200	8.02	203.7	9.47	240.5	1.10	28.0	5.63	8380	32	10	72.52	0.50	41.34	1050

\* This is a made-to-order product. Please contact our company regarding order quantities and other inquiries.

#### **Operating Temperature Range:**

°F: -14 to 122 °C: -10 to 50

#### Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

Scan, tap, or touch for product videos





# TOTAKU Hoses for Vacuum Trucks

Founded in 1952, TOTAKU INDUSTRIES, INC. has been a pioneer in the pipes and hose industry, creating the world's first flexible hose. Driven by our core principle of prioritizing customer satisfaction through exceptional quality, we continuously innovate to meet the evolving needs of our customers. At TOTAKU, we are dedicated to making a positive impact on the world by developing unique, thoughtful products that address modern challenges.

## **Featured Products**

CLEAN-W	02
CLEAN-S	03
CLEAN-CW	04
CLEAN-DC	05

#### Notice:

- The data in this catalog uses values in a straight hose configuration.
- The permissible pressure is not the maximum operating pressure. Please refer to the "Operating Pressure Design Table" in the hose handling precautions and configure according to the operating pressure (normal working pressure). Also, please note that the combination of fittings and clamps, operating temperature, and bending conditions may affect performance.

# TOTAKU CLEAN-W

 Part Number - 24107

## Soft PVC Rigid PVC Outer Dameter Diameter



## **Standard Dimensions and Properties**

Nominal Diameter		Inner Diameter		Outer Diameter		Reference Weight		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	psi	МРа	inch	mm
2	50	2.00	50.8	2.42	61.4	0.81	1200	43.51	0.30	19.69	500
2.5	65	2.50	63.5	2.99	76.0	1.20	1790	43.51	0.30	27.56	700

#### **Operating Temperature Range:**

## Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

**Discharge** °F: 14 to 122 °C: -10 to 50

°F: 14 to 140 °C: -10 to 60

Suction

#### 02 of 05 | TOTAKU Hoses for Vacuum Trucks

## Features

- The outer surface is designed for abrasion resistance, providing outstanding durability.
- Easy to wash with water, making it highly hygienic.

### Applications

• Exclusively for vacuum trucks.

## **TOTAKU CLEAN-S**



## **Standard Dimensions and Properties**

Nominal Diameter		Inner Diameter		Outer Diameter		Reference Weight		Allowable (at room ter	Pressure mperature)	Allowable Bend Radius (to the center axis of the hose)		
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	psi	МРа	inch	mm	
2	48	1.89	48.0	2.26	57.5	0.70	1035	43.51	0.30	17.72	450	

#### **Operating Temperature Range:**

## Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

°F: 14 to 140 °C: -10 to 60

## Discharge

Suction

°F: 14 to 122 °C: -10 to 50

#### 03 of 05 | TOTAKU Hoses for Vacuum Trucks

## Features

• A lightweight version of the TOTAKU CLEAN-W.

#### Applications

• Exclusively for vacuum trucks.

# TOTAKU CLEAN-CW

Part Number - 24109





#### Features

- A versatile, all-season hose designed to handle a wide range of temperature changes in working environments.
- Exceptional cold resistance, suitable for use even in cold climates. (Operating temperature range: -20°C [-4°F] to 50°C [122°F]).

#### Applications

• Exclusively for vacuum trucks.

### Cautions

• Avoid long-term storage outdoors, as this may cause cracks to form due to ozone degradation.



## **Standard Dimensions and Properties**

Nominal Diameter		Inner Diameter		Outer Diameter		Reference Weight		Length		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	lbs/ft	g/m	ft	m	psi	MPa	inch	mm
2	48	1.89	48.0	2.22	56.5	0.65	960	65/98 131/164	20/30 40/50	29.01	0.20	15.75	400

**Operating Temperature Range:** 

## °F: -4 to 122 °C: -20 to 50

Notes:

• The permissible pressure varies with operating temperature.

• Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

## **TOTAKU CLEAN-DC**

Part Number - 24108





• Specifically designed for discharge, ensuring smooth operation on-site.

## Applications

• Discharge hose exclusively for vacuum trucks.





(For Coupling on Vacuum Trucks – Allowable Pressure 29 psi [0.20 MPa] or Less)

## **Standard Dimensions and Properties**

Non Dian	ninal neter	nal Inner eter Diameter		Outer Diameter		Pitch		Reference Weight		Allowable Pressure (at room temperature)		Allowable Bend Radius (to the center axis of the hose)	
inch	mm	inch	mm	inch	mm	inch	mm	lbs/ft	g/m	psi	MPa	inch	mm
2.5	65	2.50	63.5	3.09	78.5	0.56	14.3	1.17	1740	58.02	0.40	31.50	800
3	75	3.00	76.2	3.65	92.8	0.59	15.1	1.51	2240	50.76	0.35	35.43	900

## **Operating Temperature Range:**

## Notes:

- The permissible pressure varies with operating temperature.
- Operating down to a vacuum level of approximately -29.5 inHg (-0.1 MPa) is feasible at room temperature

**Discharge** °F: 14 to 122 °C: -10 to 50

°F: 14 to 140 °C: -10 to 60

Suction

# TOTAKU INDUSTRIES, INC.

1-1-17 SHINMACHI, NISHI-KU, OSAKA CITY, OSAKA 550-8668, JAPAN